

SLATE, SANDSTONE AND OTHER DIMENSION STONES



# Indian Minerals Yearbook 2016

(Part- III : Mineral Reviews)



**55<sup>th</sup> Edition**

## SLATE, SANDSTONE AND OTHER DIMENSION STONES

**(FINAL RELEASE)**

**GOVERNMENT OF INDIA  
MINISTRY OF MINES  
INDIAN BUREAU OF MINES**

Indira Bhavan, Civil Lines,  
NAGPUR – 440 001

PHONE/FAX NO. (0712) 2565471  
PBX : (0712) 2562649, 2560544, 2560648  
E-MAIL : [cme@ibm.gov.in](mailto:cme@ibm.gov.in)  
Website: [www.ibm.gov.in](http://www.ibm.gov.in)

**February, 2018**

# 45 Slate, Sandstone & Other Dimension Stones

The principal rock types used as dimension stones other than granite and marble are slate, sandstone, limestone and quartzite. India is endowed with abundant resources of these types of dimension stones which are increasingly being used domestically. These stones are also important export commodities. India is one of the largest producers of dimensional stones in the world.

## 1. Slate

Slate is a fine-grained, very low-to-low metamorphic rock possessing a well developed fissility (splitting attitude) parallel to the planes of slaty cleavage. It is formed by the metamorphism of pre-existing clay rocks such as claystone, shale or siltstone. The most remarkable feature of this rock is that it has cleavage planes that are well marked which enable it to be split manually or mechanically into relatively thin slabs. Slate is a low-cost decorative stone used for exterior and interior decoration of buildings. It is significantly used in roofing. It is also used as school slate and also as building dimension stone. Slate has an aesthetic value like other dimension stones, granite and marble. Slate has emerged as a low cost alternative to granite and marble which are comparatively expensive. The exports of slate have increased over the years resulting in a boost to slate mining industry in the country. Micaceous and chlorite slates are generally preferred.

## OCCURRENCES

The Aravalli Mountain ranges in Rajasthan and Haryana; rock assemblages under Kadapa System in Andhra Pradesh and Tamil Nadu; and Himalayan region in Northern India have undergone metamorphism and given rise to the slate deposits along with other metamorphosed products. The availability of slates has also been reported from Madhya Pradesh, Haryana, Himachal Pradesh, Jharkhand, Andhra Pradesh, Rajasthan, Uttarakhand, Bihar and Gujarat.

## RESERVES/RESOURCES

An attempt has been made to prepare inventory of slate. This may not be completed.

The total reserves/ resources of slate as on 1.4.2015 as per UNFC system are placed at 22.9 million tonnes under unclassified grade. Reserves/ resources are located in Andhra Pradesh & Haryana (Table- 1).

## EXPLORATION & DEVELOPMENT

No exploration activities were reported for slate during 2015-16.

## PRODUCTION

As per GOI Notification S-O.423(E) dated 10.2.2015, slate has been declared as 'Minor Mineral', hence the production beyond January, 2015 is not available with IBM. List of producers of slate is furnished in Table-2.

The value of production of slate for 2014-15 decreased to ₹ 6.64 crore from ₹ 6.65 crore in 2013-14 (Table-3).

**Table –2: Producer of Slate**

Name and address of producer	Location of mine	
	State	District
Shri Ashok Somany, Khol House, Circular Road, In front of Ramlila Ground, Distt. Rewari- 123 401, Haryana.	Haryana	Rewari

**Table – 3 : Value of Production of Slate  
2012-13 to 2014-15  
(By States)**

State	(In ₹'000)		
	2012-13	2013-14	2014-15(P)
<b>India</b>	<b>20332</b>	<b>66521</b>	<b>66457</b>
Haryana	-	48687	25841
Andhra Pradesh	5922	6665	27681
Himachal Pradesh	10200	9900	8935
Jammu & Kashmir	10	-	-
Rajasthan	4200	1269	4000

*Source: State Governments.*

SLATE, SANDSTONE AND OTHER DIMENSION STONES

**Table – 1 : Reserves/Resources of Slate as on 1.4.2015  
(By Grades/States)**

(In '000 tonnes)

Grade/State	Reserves			Remaining resources					Total resources (A+B)		
	Proved STD111	Probable STD121    STD122	Total (A)	Feasibility STD211	Pre-feasibility STD221    STD222	Measured STD331	Indicated STD332	Inferred STD333		Reconnaissance STD334	Total (B)
<b>All India : Total</b>	<b>19619</b>	<b>667</b>	<b>20286</b>	<b>-</b>	<b>-</b>	<b>1075</b>	<b>-</b>	<b>1511</b>	<b>-</b>	<b>2586</b>	<b>22872</b>
<b>By Grades</b>											
Unclassified	19619	667	20286	-	-	1075	-	1511	-	2586	22872
<b>By States</b>											
Andhra Pradesh	109	667	776	-	-	1075	-	1511	-	2586	3362
Haryana	19510	-	19510	-	-	-	-	-	-	-	19510

Figures rounded off

## MINING AND PROCESSING

Mining of slate is done by opencast method. The slate bands are exposed by removing the overburden by means of drilling and controlled blasting. The mining in many places is carried out by manual means but in some mines, semi-mechanised method of mining is also adopted. After removing a thick slab of slate preferably of larger size, the slab is split using hammers, specially-made chisels and cutting knives. The saleable tile or slab of slate is obtained in 6 to 10 mm thickness for cladding and 20 to 35 mm thickness for flooring or for panels. The edges are cut manually by using machines to have a smooth and regular edge. The slate as building stone is marketed under the commercial names, such as Golden Copper, Green, Black, Panther, Mica, Speckled, Deoli, Mahi, Silver Grey and Peacock. Peacock is the only premier variety produced in Kund area, Haryana.

The overall recovery of slate is very low, being a fragile material among all the building/dimension stones. Normally, huge accumulation of broken pieces in and around the slate quarry is observed incidental to mining & processing. Proper mining and processing techniques by using modern equipment may improve the situation in future.

## USES AND SPECIFICATIONS

There are two main uses of slate as a natural stone in building work: 1) for roofing in the form of roofing tiles and 2) for flooring in the form of tiles and for cladding purposes.

For roofing tiles, the slate should be exfoliated easily and should be free from minerals like iron sulphides or carbonates which in time could cause corrosion and staining on roofing tiles. For cladding or flooring purposes, the slate should be able to bear the cutting processes in required sizes, polishing or smoothening process by machines and should not peel off during the process of fixing or laying. Bureau of Indian Standard has laid down Standard IS: 6250-1981 (First revision; reaffirmed 2008) namely, specification for roofing slate tiles with respect to requirement of dimensions, physical properties and workmanship of slate tiles used for sloped roof covering.

## 2. Sandstone

Sandstone is a sedimentary rock largely made up of sand grains in size ranging from 2 mm to 120 mm of varying compositions. The sand may consist of grains of quartz, felspar and other detrital minerals with interstitial cementing material. The composition of sand particles and the cementing material by and large defines the colour of sandstone while the mode of formation decides the thickness of bed which gives rise to various types of sandstones.

The colour of sandstone may range from dark red to brown, earthy to buff, white, yellow and a number of other shades. The pattern of the sandstone depends upon the thickness of bed. Sandstone produced in the country is being marketed as Vindhyan Red, Rainbow, Teak, Modak, Bundi, Bansi Pink, Mandana, Dholpur Cream, etc. The sandstone may occur as massive, thick, non-splittable bands or thin beds or layers that can be split by applying slight pressure.

## RESERVES/RESOURCES

Occurrences of sandstone in India are spread across Andhra Pradesh, Assam, Bihar, Gujarat, Haryana, Madhya Pradesh, Meghalaya, Mizoram, Karnataka, Odisha, Punjab, Rajasthan, Uttar Pradesh, Tamil Nadu and West Bengal.

The reserve/resource estimation has not been considered important because of its abundance and easy availability. Hence, there is no comprehensive inventory of sandstone. However, the Centre for Development of Stones (CDOS), a 'Government of Rajasthan Undertaking' has reported estimated reserves of sandstone at over 1,000 million tonnes in the country. Huge deposits of sandstone in Rajasthan are associated with Vindhyan and Trans-Aravalli Formations, exposed over an area of nearly 35,000 sq km covering districts of Dholpur, Bharatpur, Karauli, Sawai Madhopur, Tonk, Bundi, Jhalawar, Kota, Bhilwara and Chittorgarh. It is also found scattered in the districts of western desert plain in the districts of Jodhpur, Churu, Bikaner and Nagaur. Splittable sandstone deposits are confined to an area of 16,000 sq km, out of which 10,000 sq km lies in eastern and south-eastern Rajasthan and 6,000 sq km in western Rajasthan.

## SLATE, SANDSTONE AND OTHER DIMENSION STONES

In Gujarat, fine to medium-grained sandstone of varying colours ranging from white, light-purplish, reddish-brown, cream to yellow are found in the district of Kachchh. A brownish-yellow sandstone occurs near Chabari and Mainapara in Bhachau tehsil. The sandstone at Rampur, Katada-Roha and Rajoda Dungar near Mangwana in Nakhtrana tehsil is cream coloured and is fairly hard. Extensive deposits are found around Songir, Naswadi, Ghautoli, Namaria and Lachharas in district Vadodara.

The Vindhyan and Satpura Mountains in Madhya Pradesh have vast resources of sandstone. The red, cream and white sandstone are being quarried extensively in Panna and Shivpuri districts and in many areas near Jabalpur.

In Uttar Pradesh, sandstones suitable for making slabs and tiles are located in Agra, Mirzapur, Lalitpur, Allahabad and Sonbhadra districts. The sandstone of Lalitpur district is yellow, light green and maroon and takes good

polish. The sandstone in Lalitpur occurs in Madanpur and Rampura (near Deogarh) areas and is traded under the commercial name Royal Gold, Beach Sand and U.P. Green. The sandstone of Agra occurring in Tatpur area is red and mottled and is used for interior as well as exterior flooring and cladding. In Mirzapur and Sonbhadra areas, good quality buff to pale and creamish sandstone is available.

The felspathic sandstone occurring with the coal seams as overburden is also used as building stone. The Kamthi Sandstone occurring in and around tehsil Saoner, district Nagpur in Maharashtra is being quarried and is used as building stone.

### EXPLORATION & DEVELOPMENT

The DMG, Rajasthan has carried out exploration for sandstone in 2015-16. The details of exploration are furnished in Table -4.

**Table – 4: Details of Exploration Activities for Sandstone, 2015-16**

Agency/State/ District	Location/ Area	Mapping		Drilling		Sampling (No.)	Remarks/ Reserves/Resources estimated
		Scale	Area (sq km)	No. of boreholes	Meterage		
<b>DMG Rajasthan</b>							
Karauli	N/v Mundeli- Mauakhera Mundeli- Ratiyapura Chhawar, Teh. Masalpur	1:50000 1:10000 1:4000	100 10 3	-	-	4	Total reserves of splittable sandstone were estimated at 1.6 million tonnes N/v Mundeli- Mauakhera and about 0.65 million tonnes N/v Mundeli- Ratiyapura & 1.3 million tonnes in chhawar.
Barmer	N/v Harwecha, Junejo ki Dhani, Bhoja Bhakhar etc. Teh. Sheo,	1:50000 1:10000 1:4000	300 23 3	-	-	16	Thickness of sandstone was found to be 1 to 1.5 m on the surface as capping, which is useful for masonry purpose. Reserves/ Resources have not been estimated.
Jodhpur	N/v Thadia, Fathegarh, Lalsar, Gumanpura etc. Teh. Shergarh	1:50000 1:10000 1:2000	100 10 2	-	-	7	The thickness of splittable /blockable sandstone varies from 3m -4 m. 28 plots have been delineated. Reserves/Resources have not been estimated.
Jaisalmer	N/v Jajiya, Kuldhara Mayajal etc. Teh. Jaisalmer	1:50000 1:10000 1:4000	100 10 3	-	-	-	Reserves/Resources have not been calculated. Yellow limestone suitable for dimension stone in about 1 sq km area with thickness 0.50-2m was noticed.

## SLATE, SANDSTONE AND OTHER DIMENSION STONES

### PRODUCTION

Data on production of sandstone is not available. However, it is estimated that Rajasthan may be producing cent percent production in the country used for building purposes and as road metal along with quartzite. Production value of quartzite and sandstone as available is given in Table- 5.

**Table – 5: Value of Production of Quartzite & Sandstone\*, 2012-13 to 2014-15 (By States)**

State	2012-13	2013-14	2014-15 (P)
<b>India</b>	<b>7612211</b>	<b>6529443</b>	<b>7356285</b>
Haryana			6337
Himachal Pradesh	155000	1600	1335
Jammu & Kashmir	53355	7534	336
Madhya Pradesh	11179	-	-
Rajasthan	7390200	6517832	7345800
Tamil Nadu	2477	2477	2477

(In ` '000)

*Source: State Governments*

*\* Used for purposes of building or for making road metals and household utensils.*

The intensive quarrying activities in Rajasthan are in the districts of Bharatpur, Sawai Madhopur, Karauli, Tonk, Bundi, Jhalawar, Kota, Bhilwara, Chittorgarh, Jodhpur, Nagaur and Bikaner. The red and blue Lower Bhander Sandstones which are exposed over a large area of about 5,000 sq km in south-eastern Rajasthan, covering Kota, Bundi, Bhilwara, Chittorgarh districts are quarried at a number of places, important ones being Bijolia, Barisal, Navanagar, Banio-ka-Talab in Bhilwara district and Dabi, Budhpura, Umarthan in Bundi district. The splittable sandstone areas are Bhanpura, Rajpura, Kasara, Chobe-ki-Guwari, Mokanpura, Berda and Bhakri in Karauli district. Other important areas of sandstone quarrying in Dholpur, Bharatpur and Sawai Madhopur districts are Sarmathura, Bari, Baseri, Hindaun, Sapotra, Masalpur, Roopwas and

Band-Barolla. In other districts, important places are Fidusar, Sursagar, Mandor and Balesar (Jodhpur district) and Chhoti and Badi Khatau (Nagaur district).

### MINING & PROCESSING

Mining of sandstone is generally done manually by using hammers and chisels of various shapes. The overburden is removed which is in the form of soil, rubble or non-splittable sandstone. The hard non-splittable sandstone is then drilled and blasted to expose the underlying splittable sandstone. But, with the advent of sandstone cutting and polishing machines, this operation is also executed carefully to obtain Khandas or blocks for further processing in the form of slabs.

In conventional mining, the natural vertical joints present in the range from 0.6 m to 60 m is an advantage. The initial quarrying starts from these joints. After making the initial cut, blocks having 1.2 m width, 3 to 4 m length and thickness up to the nearest cleavage plane are removed. The quarrying operation in Rajasthan has gone to the depth of 50 m.

In the absence of joints, a jhiri is opened in a line by drilling closely spaced (about 15 cm apart) oblong or eye-shaped holes (duggis) of about 8 to 10 cm depth and the eye-shaped steel wedges (Gullas) are hammered in these holes by expert miners. The continuous hammering develops a crack along the holes. The mining starts from these blocks. The required length and width of the slab to be obtained are marked and cut accordingly using the same technique of wedging. The splitting of individual slab is carried out using natural bedding plane by inserting sharp wedges or by hammering alone.

A majority of quarry owners produce hand-dressed slabs and tiles in different thicknesses. But in the export market normally machine-cut tiles are in demand and the simple edge cutting machines with single or double cutters

are used for getting machine-cut tiles. The further requirement of tiles in 10 to 12 mm thickness with one side natural and other calibrated has resulted in establishing cutting and polishing units of sandstone. In Rajasthan, there are four units engaged in the production of polished sandstone tiles measuring 30 x 30 x 1 cm and 40 x 40 x 1.2 cm. The sandstone is also exported with natural, honed and polish-finishes. BIS has prescribed IS:3622-1977 (First Revision, reaffirmed 2003) as the specifications for sandstone slabs and tiles.

### 3. Dimensional Limestone

The limestone which is used as a dimension stone differs from the limestone used for cement making or for any other industrial purpose in two ways: firstly, chemical composition and secondly, the mode of occurrence. In both the types, the major constituent is calcium carbonate. But very high silica content gives limestone sufficient hardness to be utilised as a dimension or building stone. The industrial limestone occurs as massive formation with less intercalations while in case of dimensional limestone, thin-bedded deposits are preferred. Limestone which is compact and amorphous in texture is known as flaggy or splittable limestone and is quarried in the form of thin slabs ranging in thickness from 12 mm to 50 mm in ready-to-use form.

Limestone has been used since ancient times for construction of houses, flooring and for various other building purposes. In recent times, the use of limestone has increased manifold mainly in interior flooring, cobble stones and for decorative purposes in combination with other stones because of its various colours and shades. Depending upon the place of origin of limestone and its colour, various types of nomenclatures have been used in the trade for limestone, such as, Kadapa Stone, Shahabad Stone, Kota Stone with different shades and colours (Kota Blue, Kota Brown, etc.), Kachchh Stone, Miliolitic Limestone, etc.

## OCCURRENCES

Occurrences of dimensional limestone have been reported from various states such as Shahabad Stone of Vijapura, Kalaburagi and Belagavi districts in Karnataka; and 'Kadapa Stone' of Kurnool, Anantapur and Guntur districts and 'Tandur Stone' of Kadapa district, Andhra Pradesh, etc. Other coloured well-known limestones are from Betamacherla, Tadipatri, Macherla, Nereducherla and Muddimanikyam. 'Milliolitic Limestone' from Saurashtra region, 'Yellow Limestone' of Kachchh district of Gujarat, 'Kota Limestone' of Kota district and 'Yellow Limestone' of Jaisalmer district, Rajasthan are the other prime localities of dimensional limestone occurrences in India.

Rajasthan is richly endowed with the occurrence of greenish-grey 'Kota' limestone. The Kota stone has gained tremendous popularity and is widely used for flooring and cladding purposes. The important deposits of limestone are in Kota, Jhalawar, Chittorgarh and Jaisalmer districts, Rajasthan. Kota, Jhalawar, and Chittorgarh are the major producing districts of the dimensional limestone in the state. Extensive limestone deposits are found in the Upper Stage of the Lower Vindhyan, represented by limestone which has a good potential as cement-grade limestone as well as flooring stone. Certain portions of the limestone having splittable form are used extensively as flooring stones. The limestone occurs in a north-south belt from Dalla-kakhera to Nimbahera and extends into Madhya Pradesh covering a distance of about 70 km. It is fine-grained, thinly bedded and has a total thickness of about 150 m. At a few places, the major portion of the limestone deposit is suitable for cement making but there are pockets, containing splittable forms that can be used for building and flooring purposes directly.

**Yellow limestone deposits of Jaisalmer:** The yellow limestone of Jaisalmer is of Jurassic age and is found in Bada Bag, Mool Sagar and Kanod villages of Jaisalmer. It contains 42 to 51% calcium oxide and has a thickness of about 3m. It is quarried in the form of blocks

## SLATE, SANDSTONE AND OTHER DIMENSION STONES

and can be sawed into slabs and tiles. It is also termed as yellow marble as it takes reasonably good polish.

**Flaggy limestone deposits of Jhalawar and Ramganjmandi, Kota area:** It belongs to Lower Vindhyan Group and is available in plenty at Sarola Kotri Chitawa and Khokhriya-Khurd. Extensive deposits are available near Ramganjmandi, Aroliya and Parolia areas. Ramganjmandi and Jhalawar Road are the main railway stations from where the splittable limestone produced is dispatched to various parts of the country. In the last few years, export market of this limestone which is popularly known as 'Kota Stone' has also been developed.

### PRODUCTION

Data on value of production of limestone used in kilns for manufacture of lime to be used as building material is furnished in Table- 6.

### MINING AND PROCESSING

Although the mining methods as well as the processing of limestone have changed over the years, still there is a scope for improvement in mining techniques. Simultaneously, the handling of waste and utilisation of waste rock is equally essential.

The mining of Kota Stone is carried out by opencast manual methods or by semi-mechanised methods. The Kota Stone is found in the form of natural thickness ranging from 12 to 150 mm or even more. The mined out slabs are cut to size by using hammer and chisel. Diamond saws are used to cut the tiles in required thicknesses and measurements. Tiles of Kota Stone are available in various size and thickness to suit the requirement of different building projects. This stone has a good market potential.

**Table – 6: Value of Production of Limestone\*  
2012-13 to 2014-15  
(By States)**

(In `000)

State	2012-13	2013-14	2014-15 (P)
<b>India</b>	<b>12137641</b>	<b>13369120</b>	<b>20151846</b>
Andhra Pradesh	16473	17573	23181
Chhattisgarh	2860753	4084116	3664376
Gujarat	1160346	1016700	739400
Jammu & Kashmir	26283	63816	50054
Madhya Pradesh	12069	860	195818
Rajasthan	7489700	7614038	14907000
Uttarakhand	572017	572017	572017

*Source: State Governments*

\* Used in kilns for manufacture of lime to be used as building material.

### EXPLORATION & DEVELOPMENT

No exploration activities were reported for dimension limestone (used in kilns for manufacture of lime) during 2015-16.

### USES & SPECIFICATIONS

Application of Kota Stone ranges from interior flooring, wall cladding to exterior use in paving and facades for building of all kinds and types.

The Kota Stone has a natural split non-slip surface. Massive, dense and fine-grained varieties are generally durable as these are not porous. These are tough and have a crushing strength of 17.8 kg/mm<sup>2</sup> and a high compressive strength of over 2189 kg/cm<sup>2</sup>. Abrasion value of Kota Stone is 18.12 to 18.32 and it has a high resistance to delamination and failure under freezing and thawing conditions.

Bureau of Indian Standards has prescribed Specification for Limestone (Slab & Tiles) as IS : 1128 - 1974 (First Revision, reaffirmed 2008).

## 4. Other Dimensional Stones

In addition to the dimension stones already described, other dimension stones are being quarried and used for the construction of houses and other building purposes.

In Odisha, Karnataka, Goa and in parts of coastal states, laterite is quarried in huge quantities. It is utilised as bricks in the construction of houses and pavements.

Huge deposits of basalt in Maharashtra, Karnataka and Gujarat are used as building stones since ancient times. Quartzite bands occurring along with phyllite schists are also utilised for building purpose.

In addition, stone aggregates, such as broken and sized pieces of limestone, dolomite, quartzite and sandstone are mixed either with cement for building and road-making purposes or with asphalt for mending road. To utilise the huge waste generated during mining and processing, a new variety of man-made stone "Terrazo" has been developed, which is composed of stone chips set in cement, epoxy or polyacrylate and then polished. The Terrazo is an economical alternative to solid marble slabs or tiles.

## 5. Felsite

Felsite is a fine, evenly grained acid or intermediate igneous rock, usually occurring as dykes and veins in country rocks and in the parent plutonic mass. BIS has prescribed the specification IS:10874-1983 (reaffirmed 2010) for felsite grinding media and liner stones. Felsite has architectural, industrial and antiquity uses. As per GOI Notification S.O.423(E) dated 10.2.2015, felsite has been declared as 'Minor Mineral', hence the production beyond January, 2015 is not available with IBM. However, the production value of felsite was provisionally estimated at A 13.01 crore during 2015-16. List of producers of felsite is furnished in Table-7.

**Table – 7: Principal Producers of Felsite**

Name and address of producer	Location of mine	
	State	District
Smt. S. Rajee V. Raman, Flat No. G-2, "Srivara Krishan", 3 <sup>rd</sup> Main Road, V. V. Mohalla, Distt. Mysuru, Karnataka.	Karnataka	Mysuru
Shri J. Madhu, No. 164, K. R. S Road, Mogarahally, Distt. Mandya- 571 438, Karnataka.	Karnataka	Mandya

## TRADE POLICY

As per the Export-Import Policy announced for the period 2015-20; and the Foreign Trade Policy thereunder, the imports of slate blocks or slabs whether or not roughly trimmed or merely cut are restricted under heading no. 2514.

Import of crude or roughly trimmed/cut blocks or slabs of sandstone and other monumental or building stones; viz, pakur stone, stone boulders, and others, are restricted under heading no. 2516. However, sets of curbstones and flagstones of natural stone (except slate) under heading no. 6801 and worked monumental building stone (excluding slate), tiles, cubes and similar articles of natural stone including slate, under heading no. 6802 can be imported freely. Worked slate and articles of slate or of agglomerated slate under sub-heading 6803 can also be imported freely. Exports of stone aggregates which are restricted under Chapter 25 of ITC (HS), 2015-20, Schedule 2-Export policy, are permitted to be exported to Maldives subject to ceiling limits. The limits are 5.5 lakh tonnes and 6 lakh tonnes for the years 2015-16 and 2016-17, respectively. The annual ceilings are monitored by CAPEXIL subject to exporters obtaining appropriate clearances.

## WORLD REVIEW

Reserves of slate and other dimension stones are substantial in the world. Spain was the major exporting country for dimension stones in the world. Other important exporters of slate were China, Italy, India and Brazil. Major importers of slate were Germany, UK, USA and France.

## FOREIGN TRADE

### Exports

Exports of building and monumental stones (NES) decreased considerably to 5.13 million tonnes in 2015-16 from 6.13 million tonnes in 2014-15. Quantity-wise, Bangladesh was the leading buyer accounting for 69% of the total exports, followed by Maldives (24%), UK (2%) and Belgium (1%). Value-wise, Bangladesh was also the leading buyer, contributing 23% to total value of exports, followed by UK(17%) and USA(12%) (Table- 8).

## SLATE, SANDSTONE AND OTHER DIMENSION STONES

In 2015-16, the total exports of slate decreased slightly to 98 thousand tonnes from 100 thousand tonnes in 2014-15. Out of the total exports of slate during 2015-16, 20,461 (21%) tonnes was of slate (worked), while the bulk of exports, i.e., 77,130 tonnes (79%) was of slate (others). USA was the leading buyer, accounting for over 39% value of the total slate exported followed by UK (12%) and Canada (4%). (Tables- 9 to 11).

In 2015-16, the exports of sandstone increased slightly to 0.74 million tonnes from 0.63 million tonnes in the previous year. Quantity-wise, UK was the leading buyer in 2015-16 with 57% of the total sandstone exported followed

by Belgium with 7% and value-wise also UK was the leading buyer with 62% and USA 7%. (Table- 12).

### Imports

During 2015-16, imports of building & monumental stones (NES) decreased considerably to 0.52 million tonnes from 0.76 million tonnes in the previous year. Bangladesh was the leading supplier contributing 80% to the total value of imports followed by China (4%). (Table- 13).

Imports of slate during 2015-16 were 134 tonnes compared to 472 tonnes in 2014-15. Imports of sandstone were 26 tonnes reported during year 2015-16 (Tables-14 and 15).

**Table – 8: Exports of Building and Monumental Stones, NES (By Countries)**

Country	2014-15		2015-16 (P)	
	Qty (t)	Value ( ` '000)	Qty (t)	Value ( ` '000)
<b>All Countries</b>	<b>6127052</b>	<b>7786183</b>	<b>5133276</b>	<b>8489454</b>
Bangladesh	2484016	778594	3559046	1967431
UK	135067	2043920	97133	1446824
Maldives	3129557	879114	1229162	1337007
USA	63302	951878	32552	1017688
Belgium	80444	541792	72814	465761
Canada	8053	209890	14331	337395
Qatar	2742	116567	3645	273933
France	41528	309684	27605	186900
Germany	22558	263486	14422	181163
Italy	16217	220409	13294	148204
Other countries	143568	1470849	69272	1127148

**Table – 9 : Exports of Slate (By Countries)**

Country	2014-15		2015-16 (P)	
	Qty (t)	Value ( ` '000)	Qty (t)	Value ( ` '000)
<b>All Countries</b>	<b>100447</b>	<b>1867164</b>	<b>97591</b>	<b>1927308</b>
USA	41061	815340	38880	760783
UK	18906	215556	21076	236269
Canada	4513	96531	2994	72552
Germany	1693	79710	1313	61205
Indonesia	1314	31056	1905	55040
Chinese Taipei/ Taiwan	288	25602	769	53689
Spain	1124	28309	1080	43639
Thailand	820	24354	1495	38345
Italy	1324	25447	1638	36582
China	154	15378	213	35976
Other countries	29250	509881	26228	533228

SLATE, SANDSTONE AND OTHER DIMENSION STONES

**Table – 10 : Exports of Slate (Others)  
(By Countries)**

Country	2014-15		2015-16 (P)	
	Qty (t)	Value ( ` '000)	Qty (t)	Value ( ` '000)
<b>All Countries</b>	<b>76525</b>	<b>1207337</b>	<b>77130</b>	<b>1224114</b>
USA	28897	533316	26337	448176
UK	17260	174268	19665	202749
Canada	3750	77718	2493	50753
Indonesia	1087	24269	1733	48623
Australia	2956	30577	2613	30861
Spain	830	13645	751	30130
Mexico	1865	29020	1217	26523
Thailand	466	10141	1112	26325
UAE	785	10963	1554	25858
Mauritius	973	13183	1515	22217
Other countries	17656	290237	18140	311899

**Table – 11 : Exports of Slate (Worked)  
(By Countries)**

Country	2014-15		2015-16 (P)	
	Qty (t)	Value ( ` '000)	Qty (t)	Value ( ` '000)
<b>All Countries</b>	<b>23922</b>	<b>659827</b>	<b>20461</b>	<b>703194</b>
USA	12164	282024	12543	312607
Germany	435	62430	312	44125
Chinese Taipei/ Taiwan	84	23333	141	37040
China	7	2036	94	34128
UK	1646	41288	1411	33520
Canada	763	18813	501	21799
Italy	219	10586	263	16522
France	162	6360	146	14004
Spain	294	14664	329	13509
Poland	418	14263	189	13315
Other countries	7730	184030	4532	162625

**Table – 12 : Exports of Sandstone  
(By Countries)**

Country	2014-15		2015-16 (P)	
	Qty (t)	Value ( ` '000)	Qty (t)	Value ( ` '000)
<b>All Countries</b>	<b>627008</b>	<b>8523123</b>	<b>744657</b>	<b>10161784</b>
UK	355039	5220718	427974	6348491
USA	27433	449763	41022	700420
Belgium	33527	283952	52606	350047
Canada	21272	386230	17699	339781
Germany	25197	263064	32293	334325
France	14457	126944	31547	220466
UAE	18569	214134	15178	214981
Ireland	9346	125805	15722	205148
Australia	16373	253908	12708	202332
Italy	26255	241209	19355	199843
Other countries	79540	957396	78553	1045950

SLATE, SANDSTONE AND OTHER DIMENSION STONES

**Table – 13: Imports of Building and Monumental Stones, NES  
(By Countries)**

Country	2014-15		2015-16 (P)	
	Qty (t)	Value (` '000)	Qty (t)	Value (` '000)
<b>All Countries</b>	<b>759539</b>	<b>1438610</b>	<b>521202</b>	<b>1138893</b>
Bangladesh	577061	933989	509947	911940
China	2755	63771	634	42461
Greece	1279	7394	4331	27177
Indonesia	559	31327	365	23806
UK	2282	26594	1786	20344
Italy	763	25055	92	18845
Bulgaria	-	-	2600	17079
Hong Kong	82	6556	103	14745
Germany	490	28836	381	13638
Spain	239	7426	198	12875
Other countries	174029	307662	765	35983

**Table – 14: Imports of Slate  
(By Countries)**

Country	2014-15		2015-16 (P)	
	Qty (t)	Value (` '000)	Qty (t)	Value (` '000)
<b>All Countries</b>	<b>472</b>	<b>16814</b>	<b>134</b>	<b>11295</b>
China	350	11085	107	8714
Germany	++	64	5	1850
Hong Kong	-	-	1	356
UK	1	189	20	184
USA	-	-	1	133
Belgium	-	-	++	56
Bahrain	-	-	++	2
Canada	120	5278	-	-
Italy	1	103	-	-
Spain	++	71	-	-
Other countries	++	24	-	-

SLATE, SANDSTONE AND OTHER DIMENSION STONES

**Table – 15 : Imports of Sandstone  
(By Countries)**

Country	2014-15		2015-16 (P)	
	Qty (t)	Value (` '000)	Qty (t)	Value (` '000)
<b>All Countries</b>	<b>++</b>	<b>18</b>	<b>26</b>	<b>3101</b>
Bangladesh	-	-	2	2581
UK	-	-	24	520
China	++	18	-	-

## FUTURE OUTLOOK

Slate is mostly used as a roofing material, but other uses like cladding and flooring tiles are also gaining momentum. Slates occur widespread in the country and detailed study is required to be conducted to quantify the resources. The demand for dimension stones including sandstone & others and stone products is anticipated to grow at around 15%. A similar growth is also expected in exports.

The demand for artifacts, especially carved work is on the rise all over the world. India with its rich tradition of craftsmanship and trained artisans can embark upon the world market.

Improved quarrying, finishing and hauling technology, availability of greater variety of stones and the rising cost of alternative construction materials are among the factors that suggest a consistent increase in demand for dimension stones in future.