

APATITE AND ROCK PHOSPHATE



# Indian Minerals Yearbook 2016

(Part-III : Mineral Reviews)



**55<sup>th</sup> Edition**

## APATITE AND ROCK PHOSPHATE

**(FINAL RELEASE)**

**GOVERNMENT OF INDIA  
MINISTRY OF MINES  
INDIAN BUREAU OF MINES**

Indira Bhavan, Civil Lines,  
NAGPUR – 440 001

PHONE/FAX NO. (0712) 2565471  
PBX : (0712) 2562649, 2560544, 2560648  
E-MAIL : [cme@ibm.gov.in](mailto:cme@ibm.gov.in)  
Website: [www.ibm.gov.in](http://www.ibm.gov.in)

**February, 2018**

# 1 Apatite and Rock Phosphate

---

**A**patite is the most abundant crystalline phosphate mineral found as an accessory mineral in practically all kinds of igneous rocks. Sometimes, it is concentrated in pegmatites, metallic veins and magmatic deposits. It also occurs in metamorphic rocks and as a secondary mineral in phosphatic rocks of sedimentary origin. It is a group of phosphate minerals, usually referring to hydroxylapatite, fluorapatite and chlorapatite. Moon rocks collected by astronauts during the Apollo Programme also contained traces of apatite. Fluorapatite  $\text{Ca}_5(\text{PO}_4)_3\text{F}$  is the most common variety of apatite and also a secondary source of fluorine. Collophane ( $\text{Ca}_3\text{P}_2\text{O}_8$ ) is apparently a cryptocrystalline or amorphous calcium phosphate complex. Rock phosphates or phosphorites are sedimentary phosphatic deposits comprising fine-grained mixture of various calcium phosphates, most important being hydroxyl-apatite, carbonate-apatite, fluorapatite and their solid solutions. About 80% phosphate production in the world is derived from phosphate rocks (phosphorite) containing one or more phosphatic minerals, usually calcium phosphate of sufficient purity and quantity to permit its use directly or after concentration in manufacturing commercial products.

Phosphate rock is also the source of by-product fluorine. Apatite & rock phosphate containing 3 to 4%  $\text{CaF}_2$  are useful for recovery of fluorite. Hydrofluoro-silicic acid is recovered as by-product from phosphoric acid plants during processing of rock phosphate. Phosphate rocks are also considered as a significant and secondary resource of uranium.

India is deficient in Apatite & Rock Phosphate availability. In case of apatite, the country is fully dependent upon imports, while the Rock Phosphate production is only from two states namely, Rajasthan and Madhya Pradesh.

## RESOURCES

### Apatite

The total Reserves/Resources of apatite as per NMI data, based on UNFC system as on 1.4.2015 have been placed at 24.05 million tonnes. Out of these resources, the Reserves are placed at 0.03 million tonnes, while 24.02 million tonnes are placed under Remaining Resources category. Of the total reserves/resources, West Bengal accounts for the bulk of 57%, followed by Jharkhand (30%) and Meghalaya (5%). The

remaining 8% resources are located in Rajasthan, Andhra Pradesh, Gujarat and Tamil Nadu. Gradewise, soil reclamation grade accounts for 53% followed by beneficiable grade (28%), Low, Non-beneficiable grade (13%) and remaining blendable, unclassified & not-known grades (6%). The resources of chemical fertilizer grade are over one percent (Table-1).

### Rock Phosphate

The total reserves/resources of rock phosphate as per NMI data, based on UNFC system as on 1.4.2015 have been placed at 312.67 million tonnes. Out of these, the reserves constitute only 45.80 million tonnes while 266.87 million tonnes are under Remaining Resources category. Of the total reserves/resources, 34% are in Jharkhand, 31% in Rajasthan, 19% in Madhya Pradesh, 8% in Uttar Pradesh & Uttarakhand each, respectively. Meagre quantities of resources are also located in Gujarat and Meghalaya. Gradewise, low-grade account for 37%, followed by beneficiable (29%), blendable (11%), chemical fertilizer & soil reclamation (8% each) and remaining unclassified and not-known grades (about 7%) (Table-2).

## EXPLORATION & DEVELOPMENT

Exploration activities for apatite and phosphorite/rock phosphate carried out by the RSMML, Rajasthan and GSI during 2015-16 are furnished in Table - 3.

## PRODUCTION, STOCKS & PRICES

### Apatite

The production of apatite at 150 tonnes during 2015-16 decreased by 84% as compared to that in the previous year. In both the years, production is reported by single private sector mine from Andhra Pradesh (Tables - 4, 5 & 6).

The mine-head closing stock of apatite for the year 2015-16 was 6,691 tonnes as against 6,581 tonnes in the previous year (Table- 7). The domestic prices of apatite are furnished in the General Review on 'Prices'.

The average daily labour strength employed in apatite mines during 2015-16 was 86 as against 118 in the previous year.

APATITE AND ROCK PHOSPHATE

**Table – 1 : Reserves/Resources of Apatite as on 1.4.2015  
(By Grades/States)**

(In tonnes)

State/Grade	Reserves				Remaining Resources							Total Resources (A+B)
	Proved STD111	Probable STD121	Feasibility STD211	Total (A)	Pre-feasibility STD221	Measured STD331	Indicated STD332	Inferred STD333	Reconnaissance STD334	Total (B)		
<b>All India : Total</b>	<b>27715</b>	<b>1680</b>	<b>1385734</b>	<b>29395</b>	<b>491818</b>	<b>1225345</b>	<b>2281521</b>	<b>11481250</b>	<b>6132768</b>	<b>1017646</b>	<b>24016082</b>	<b>24045477</b>
<b>By Grades</b>												
Chemical Fertilizer	27715	1680	-	29395	-	-	30000	-	200163	-	230163	259558
Soil Reclamation	-	-	1385734	-	491818	1225345	2233500	6243000	1131430	-	12710827	12710827
Low/Non-beneficial	-	-	-	-	-	-	3360	2363000	50000	666646	3083006	3083006
Beneficial	-	-	-	-	-	-	12477	1875250	4561175	351000	6799902	6799902
Blendable	-	-	-	-	-	-	2184	-	-	-	2184	2184
Unclassified	-	-	-	-	-	-	-	1000000	-	-	1000000	1000000
Non-known	-	-	-	-	-	-	-	-	190000	-	190000	190000
<b>By States</b>												
Andhra Pradesh	27715	1680	-	29395	-	-	-	-	200163	-	200163	229558
Gujarat	-	-	-	-	-	-	-	-	-	351000	351000	351000
Jharkhand	-	-	-	-	-	-	2110000	1620000	3540000	-	7270000	7270000
Meghalaya	-	-	-	-	-	-	-	-	1300000	-	1300000	1300000
Rajasthan	-	-	-	-	-	-	51521	1016000	-	-	1067521	1067521
Tamil Nadu	-	-	-	-	-	-	-	-	240000	-	240000	240000
West Bengal	-	-	1385734	-	491818	1225345	120000	8845250	852605	666646	13587398	13587398

Figures rounded off.

APATITE AND ROCK PHOSPHATE

**Table – 2 : Reserves/Resources of Rock Phosphate as on 1.4.2015  
(By Grades/States)**

(In tonnes)

State/Grade	Reserves				Remaining Resources								Total Resources (A+B)
	Proved STD111	Probable STD121	Total STD122	Total (A)	Feasibility STD211	Pre-feasibility STD221	Measured STD331	Indicated STD332	Inferred STD333	Reconnaissance STD334	Total (B)		
<b>All India : Total</b>	<b>43832936</b>	<b>5179</b>	<b>1969370</b>	<b>45807485</b>	<b>10679080</b>	<b>36271671</b>	<b>25008353</b>	<b>2912633</b>	<b>3549750</b>	<b>185771368</b>	<b>2678275</b>	<b>266871130</b>	<b>312678615</b>
<b>By Grades</b>													
Chemical Fertilizer	8612446	5179	439204	9056829	-	12936477	1682389	-	15000	2284379	-	16918245	25975074
Blendable	10446537	-	477000	10923537	6394650	-	5849933	13333	-	12092513	-	24350429	35273966
Soil Reclamation	-	-	-	-	705867	251437	7672812	732800	10000	16887166	-	26260082	26260082
Beneficiable	24773953	-	1053166	25827119	3578563	23083757	6976076	2166500	2784750	25288989	20750	63899385	89726504
Low grade	-	-	-	-	-	-	-	-	-	115547549	-	115547549	115547549
Unclassified	-	-	-	-	-	2827143	-	740000	-	10095773	2657525	16320441	16320441
Not-known	-	-	-	-	-	-	-	-	-	3575000	-	3575000	3575000
<b>By States</b>													
Gujarat	-	-	-	-	-	-	-	-	-	314820	-	314820	314820
Jharkhand	-	-	-	-	-	-	-	-	-	107370000	-	107370000	107370000
Madhya Pradesh	5999399	5179	1492370	7496948	6460616	14981336	15702042	-	2730000	10629258	50625	50553877	58050825
Meghalaya	-	-	-	-	-	-	-	-	-	1311035	-	1311035	1311035
Rajasthan	37833537	-	477000	38310537	1154961	20857437	4453355	152633	79750	28043783	2627650	57369569	95680106
Uttar Pradesh	-	-	-	-	-	432898	3118586	-	740000	21481960	-	25773444	25773444
Uttarakhand	-	-	-	-	3063503	-	1734370	2760000	-	16620513	-	24178386	24178386

Figures rounded off.

APATITE AND ROCK PHOSPHATE

**Table – 3 : Details of Exploration Activities for Apatite & Phosphorite/ Rock Phosphate  
During 2015-16**

Agency/ State/District	Location	Mapping		Drilling		Sampling No.	Remarks Reserves/Resources estimated
		Scale	Area ( sq km)	No. of boreholes	Meterage		
<b>RSMML</b>							
<b>Rock Phosphate</b>							
<b>Rajasthan</b>							
Udaipur	A Ext , F & E blocks at Jhamarkotra mine	-	1370.369	27	3168	-	The objective of exploration was to establish the continuity of phosphate ore at depth and strike for mine planning. The strike length is about 12.06 km with dip varying from sub vertical to about 30 degree. Structurally, folded and undulating ore bed dipping towards the centre of Jhamarkotra basin. As on 1.4.2016, total resources were estimated at 46.727 million tonnes and Reserves were estimated at 26.093 million tonnes.
<b>GSI</b>							
<b>Phosphorite</b>							
<b>Rajasthan</b>							
Banswara	Sallopat block	1:12500 1: 2000	100 1.00	9	334.50	433 (Chemical analysis)  5 (petrographic studies)	The important litho units noticed during detailed mapping are stromatolitic dolomite (phosphatic)/ dolomite, chert, quartzite and calcareous sandstone (slightly phosphatic). Stromatolites of columnar, bedded, laminated, fragmentary and brecciated types are noticed. Stromatolite bearing dolomite occurs as lensoidal bodies of varying dimensions (50 m to 350 m). Mainly two generations of dolomite have been noticed in the Sallopat area - the older grey to bluish grey dolomite is mainly stromatolite-bearing (phosphatic) and it is capped by younger generations of barren dolomite. A fresh zone of stromatolite-bearing dolomite of about 10 to 15 m is exposed in Khunda Galla area in the NW extension of Sallopat Block. A 1.5 km long stromatolite-bearing dolomite has been traced in Sallopat area with a width of about 50 to 600 m, which is noticed on either side of Pat nala. Stromatolitic zones are also noticed in Shivpura, Jher Moti, Ram Ka Munna and Rola areas. The important lithounits intersected in boreholes are bluish grey stromatolitic dolomite (phosphatic), grey to greyish white dolomite (slightly phosphatic), pinkish dolomite, chert/cherty quartzite and quartz veins. In general, the stromatolite-bearing dolomite is intersected at a depth of 0.00-20.00 m. Mostly bluish grey stromatolitic dolomite is phosphatic in nature.

APATITE AND ROCK PHOSPHATE

**Table – 4 : Producers of Apatite, 2015-16**

Name and address of producer	Location of mine	
	State	District
Andhra Phosphate (Pvt.) Ltd, 45-58-17/5, Narasimha Nagar, Visakhapatnam-530 024, Andhra Pradesh.	Andhra Pradesh	Visakhapatnam

**Table – 5 : Production of Apatite, 2013-14 to 2015-16  
(By States)**

(Quantity in tonnes; Value in `'000)

State	2013-14		2014-15		2015-16 (P)	
	Quantity	Value	Quantity	Value	Quantity	Value
<b>India/Andhra Pradesh</b>	<b>1300</b>	<b>2768</b>	<b>930</b>	<b>2065</b>	<b>150</b>	<b>332</b>

**Table – 6 : Production of Apatite, 2014-15 and 2015-16  
(By Sectors/States/Districts/Grades)**

(Quantity in tonnes; Value in `'000)

State/District	2014-15			2015-16 (P)		
	No. of mines	Quantity	Value	No. of mines	Quantity	Value
<b>India</b>	<b>2</b>	<b>930</b>	<b>2065</b>	<b>2</b>	<b>150</b>	<b>332</b>
Public sector	1*	-	-	1*	-	-
Private sector	1	930	2065	1	150	332
<b>Andhra Pradesh</b>	<b>1</b>	<b>930</b>	<b>2065</b>	<b>1</b>	<b>150</b>	<b>332</b>
Visakhapatnam	1	930	2065	1	150	332
<b>West Bengal</b>	<b>1*</b>	<b>-</b>	<b>-</b>	<b>1*</b>	<b>-</b>	<b>-</b>
Purulia	1*	-	-	1*	-	-

\* Only labour reported.

APATITE AND ROCK PHOSPHATE

**Table – 7 : Mine-head Closing Stocks of Apatite, 2014-15 & 2015-16  
(By States/Grades)**

State	2014-15	2015-16 (P)
<b>India</b>	<b>6581</b>	<b>6691</b>
Andhra Pradesh	275	385
West Bengal	6306	6306

**Phosphorite/Rock Phosphate**

The total production of phosphorite/rock phosphate at 1,474 thousand tonnes in 2015-16 decreased by about 8% as compared to that in the previous year.

There were 5 reporting mines in both the years. Rajasthan continued to be the principal producing state, contributing 96% of the total production and the remaining 4% was contributed by Madhya Pradesh.

About 62% of the total production of phosphorite/rock phosphate was of grade upto 20% P<sub>2</sub>O<sub>5</sub>, 34% of

grade above 30% P<sub>2</sub>O<sub>5</sub> and 2% each of grade above 25% to 30% P<sub>2</sub>O<sub>5</sub> and above 20% to 25% P<sub>2</sub>O<sub>5</sub>. (Tables-8 to 10).

The mine-head closing stocks of Phosphorite/Rock Phosphate in year 2015-16 were 2,566 thousand tonnes as compared to 2,356 thousand tonnes in 2014-15 (Table-11). Domestic prices are furnished in the General Review on 'Prices'.

The average daily labour employed in phosphorite/rock phosphate mines in 2015-16 was 962 as against 1,111 in the previous year.

**Table – 8 : Principal Producers of Phosphorite/Rock Phosphate, 2015-16**

Name and address of producer	Location of mine	
	State	District
Rajasthan State Mines & Minerals Ltd, C-89/90, Janpath, Lal Kothi Scheme, Jaipur-302 004, Rajasthan.	Rajasthan	Udaipur
Hindustan Zinc Ltd, Yashad Bhavan, Udaipur-313 004, Rajasthan.	Rajasthan	Udaipur
Madhya Pradesh State Mining Corp. Ltd, Block A, 2 <sup>nd</sup> Floor, Paryawas Bhavan, Jail Road, Arera Hills, Bhopal - 462 011, Madhya Pradesh.	Madhya Pradesh	Chhatarpur Sagar

APATITE AND ROCK PHOSPHATE

**Table – 9 : Production of Phosphorite/Rock Phosphate, 2013-14 to 2015-16  
(By States)**

(Quantity in tonnes; Value in `'000)

State	2013-14		2014-15		2015-16 (P)	
	Quantity	Value	Quantity	Value	Quantity	Value
<b>India</b>	<b>1453580</b>	<b>4754755</b>	<b>1607215</b>	<b>3759071</b>	<b>1473722</b>	<b>3275250</b>
Madhya Pradesh	131465	145137	79264	67263	66293	50804
Rajasthan	1322115	4609618	1527951	3691808	1407429	3224446

**Table – 10 : Production of Phosphorite, 2014-15 and 2015-16  
(By Sectors/States/Districts/Grades)**

(Quantity in tonnes; Value in `'000)

State/ District	No. of mines	2014-15					2015-16 (P)							
		Grade: P <sub>2</sub> O <sub>5</sub> content				Total		Grade: P <sub>2</sub> O <sub>5</sub> content				Total		
		Above 30%	Above 25- 30%	Above 20- 25%	Upto 20%	Qty	Value	No. of mines	Above 30%	Above 25- 30%	Above 20- 25%	Upto 20%	Qty	Value
<b>India</b>	<b>5</b>	<b>455621</b>	<b>118280</b>	<b>25221</b>	<b>1008093</b>	<b>1607215</b>	<b>3759071</b>	<b>5</b>	<b>503045</b>	<b>25943</b>	<b>30875</b>	<b>913859</b>	<b>1473722</b>	<b>3275250</b>
Public														
Sector	4	455621	1924	-	1008093	1465638	3394600	4	503045	288	-	913859	1417192	3174027
Private														
Sector	1	-	116356	25221	-	141577	364471	1	-	25655	30875	-	56530	101223
<b>Madhya Pradesh</b>	<b>3</b>	<b>-</b>	<b>1924</b>	<b>-</b>	<b>77340</b>	<b>79264</b>	<b>67263</b>	<b>3</b>	<b>-</b>	<b>288</b>	<b>-</b>	<b>66005</b>	<b>66293</b>	<b>50804</b>
Chhatarpur	1	-	1752	-	26023	27775	21683	1	-	238	-	26062	26300	20863
Jhabua	1	-	-	-	19598	19598	21636	1	-	-	-	-	-	-
Sagar	1	-	172	-	31719	31891	23944	1	-	50	-	39943	39993	29941
<b>Rajasthan/ Udaipur</b>	<b>2</b>	<b>455621</b>	<b>116356</b>	<b>25221</b>	<b>930753</b>	<b>1527951</b>	<b>3691808</b>	<b>2</b>	<b>503045</b>	<b>25655</b>	<b>30875</b>	<b>847854</b>	<b>1407429</b>	<b>3224446</b>

\* Only labour reported.

**Table – 11 : Mine-head Closing Stocks of Phosphorite/Rock Phosphate, 2014-15 & 2015-16  
(By States/Grades)**

(In tonnes)

State	2014-15					2015-16 (P)				
	Grade: P <sub>2</sub> O <sub>5</sub> content				Total	Grade: P <sub>2</sub> O <sub>5</sub> content				Total
	Above 30%	Above 25-30%	Above 20-25%	Upto 20%		Above 30%	Above 25-30%	Above 20-25%	Upto 20%	
<b>India</b>	<b>709751</b>	<b>156038</b>	<b>113281</b>	<b>1376458</b>	<b>2355528</b>	<b>719923</b>	<b>55289</b>	<b>141803</b>	<b>1648922</b>	<b>2565937</b>
Madhya Pradesh	-	148	-	5630	5778	-	113	-	31511	31624
Rajasthan	709751	155890	113281	1370828	2349750	719923	5176	141803	1617411	2534313



## MINING AND MARKETING

Apatite mining is confined to Visakhapatnam district, Andhra Pradesh and in Purulia district, West Bengal. In apatite mine of Andhra Phosphate (Pvt.) Ltd, manual mining was carried out by developing benches along the strike length, following the dip of ore body, and by lateral developments of levels along the strike. A mineral treatment plant at Srungavarapukota, about 20 km from the apatite mine has two disintegration units of 15 hp and 50 hp that operate from two separate sheds. Apatite after disintegration is screened to 40 mesh, 60 mesh and 100 mesh. The screened material of right size is packed in quantities of 50 kg each in polythene-lined gunny bags and are despatched for sale to buyers through Srungavarapukota railway station.

West Bengal Mineral Development & Trading Corporation (WBMDTC) operates the only apatite mine in West Bengal which is located at Beldih. The mine is operated by using opencast mining method with the deployment of HEMM like JCB excavator, jackhammer drills, air compressor, tippers, etc. The mine has a production capacity of about 15,000 tonnes of in situ ore per annum. Half of the low-grade ore (10-12%  $P_2O_5$ ) is blended with available high-grade ore (>22%  $P_2O_5$ ) manually to produce additional quantity of saleable ore (18-20%  $P_2O_5$ ). The desired grade (18-20%  $P_2O_5$ ) of apatite ore is ground to 100 mesh and sold in the local market for direct application in the name of "PURULIA PHOS". However, no production was reported for the year 2014-15 & 2015-16.

In the case of rock phosphate, the production of phosphorite/rock phosphate in India was reported from four State Public Sector mines. Of these, Chhatarpur, Sagar and Jhabua districts of Madhya Pradesh have one mine each, while Udaipur district of Rajasthan has the fourth mine. The one mine under the Private Sector is also located at Udaipur district in Rajasthan.

The Meghnagar mine in Jhabua district and Hirapur mine in Chhatarpur and Sagar districts of Madhya Pradesh are worked by opencast method and both the mines are operated by Madhya Pradesh State Mining Corporation Ltd. Compressed-air jack hammers are

deployed for drilling. The present run-of-mine capacity of Jhabua mine is 1,50,000 tonnes per year. The entire ore produced from this mine is directly sold to private beneficiation companies namely, AP India Biotech Ltd and M/s. Krishna Posphochem Ltd, whose plants are located about 22 km from the mine having the total production capacity of 200,000 tonnes per annum of Beneficiated rock phosphate. The BRP plant at Hirapur mine is operated by Madhya Bharat Agro Industries Ltd. The processed ore from the plant is predominantly sold to manufacturers of phosphatic fertilizers and chemicals. Some parts of the ore are also internally consumed for fertilizer production.

In Rajasthan, the ore body at Jhamarkotra mine of M/S RSMML extends over a strike length of 10 km and the average width of phosphate bed is about 15 m with an average inclination of about  $55^\circ$  from the vertical. The height of the bench is maintained up to 10 m. Shovels (6.1 cu m) and dumpers (85 tonnes) are used for removal of ore and overburden. The mine has an annual rock handling capacity of about 20 million tonnes. The thin and sharply dipping ore body results in long and narrow pits with great depth extension which leads to very high stripping ratio (about 1:10) with high lead distance and lift for waste and mineral. An effective dewatering scheme was implemented to tackle ground water problem. The working levels are kept dry by continuous pumping of ground water through tube-wells constructed on periphery of the pit limit. The beneficiation plant of RSMML at Jhamarkotra has 9 lakh tpy capacity to treat run-of-mine low-grade ore, with an average 16%  $P_2O_5$ . Production from Jhamarkotra mine is despatched to many phosphatic fertilizer and chemical manufacturers from Udaipur and Umra railway stations which are located at 18 km and 25 km, respectively, away from the mine.

RSMML produces the following products:

- (1) (+)30%  $P_2O_5$  crushed -1/2" size high-grade rock phosphate (for SSP manufacturing units).
- (2) 31.5%  $P_2O_5$  high-grade rock phosphate Chips (for DAP/Phos Acid manufacturing units).
- (3) 18%  $P_2O_5$  ground low-grade beneficiated rock phosphate (RAJPHOS) (direct application to acidic soils).
- (4) 31.54%  $P_2O_5$  - BRP Grade (for SSP & DCP Manufacturing units, PROM etc.)

M/s. RSMML was unable to market its low-grade rock phosphate (trade name-Rajphos) till 2005-06 because of its high  $R_2O_3$  content which could neither be blended nor beneficiated. However, during recent years, this grade of rock phosphate has found takers especially, fertilizer manufacturers.

## INDUSTRY

Presently, there are about 30 large size UREA, 32 DAP and complex, 104 SSP and 2 ammonium sulphate plants.

Among the major fertilizer products, the production of UREA was 24.48 million tonnes (7.08 million tonnes from public sector, 6.94 million tonnes from cooperative sector and 10.45 million tonnes from private sector), Diamonium Phosphate (DAP) 3.79 million tonnes (1.67 million tonnes from cooperative sector and 2.11 million tonnes from private sector), (Nitrogen, Phosphorus and Potash) NP/NPK complex fertilizers 8.30 million tonnes (1.20 million tonnes from public sector, 2.29 million tonnes from cooperative sector and 4.81 million tonnes from private sector) during 2015-16.

The major phosphatic fertilizer plants in Public Sector are Fertilizers and Chemicals (Travancore) Ltd (FACT) at Udyogamandal, Kochi (Kerala); Rashtriya Chemicals and Fertilizer Ltd (RCF) at Trombay, Mumbai (Maharashtra); Madras Fertilizer Limited at Chennai (Tamil Nadu), Brahmaputra Valley Fertilizers Corporation Ltd (BVFCL) at Namrup (Assam) National Fertilizers Ltd. (NFL) at Noida, FCI Aravalli Gypsum and Minerals India Ltd. (FAGMIL) at Jodhpur (Rajasthan), Projects and Development India Limited (PDIL) at Noida, Fertilizer Corporation of India Limited (FCIL) in New Delhi and Hindustan Fertilizer Corporation Ltd. (HFCL) in New Delhi.

The plants in Private Sector are Gujarat State Fertilizer Company Ltd (GSFC) at Vadodara (Gujarat); Zuari Agro Chemicals Ltd in Goa; Mangalore Chemicals and Fertilizers & Chemicals Ltd at Mangaluru (Karnataka); Gujarat Narmada Valley Fertilizers & Chemicals Ltd (GNFC) at Bharuch (Gujarat); Nagarjuna Fertilizer and Chemicals Ltd (NFCL) at Kakinada (Hyderabad), Chambal Fertilizers and Chemicals (CFCL) at Gadepan (Rajasthan); Tata Chemicals Ltd (TCL) Bardala (Uttar Pradesh); Kanpur Fertilizer and Cements Ltd (KFCL) at Kanpur (Uttar Pradesh); Indo-Gulf Fertilizers Limited Jagdishpur Uttar Pradesh etc.

The plants in the Co-operative Sector to manufacture phosphatic fertilizer are Indian Farmers Fertilizer Co-operative Ltd (IFFCO) at Kandla (Gujarat) and Krishak Bharti Cooperative Ltd (KRIBCHO) at Surat (Gujarat). The 2 plants of IFFCO are in Gujarat (Kalol and Kandla), 2 in Uttar Pradesh (Phulpur and Aonla) and one in Odisha (Paradeep).

Besides, M/s. RSMML has a beneficiation plant in Jhamarkotra in Rajasthan, while M/s. Krishna Phoschem Ltd has set up a 600 tpd rock phosphate beneficiation plant at Meghnagar in Jhabua district of Madhya Pradesh. The Company has long-term tie-up with Madhya Pradesh State Mining Corporation Ltd.

The other associate industries on rock phosphate include Coimbatore Pioneer Fertilizer Ltd and Rashtriya Chemicals & Fertilizers Ltd, Mumbai which have domestic plants that recover by-product fluorine from rock phosphate in the form of hydrofluorosilicic acid, sodium silico-fluoride; and aluminium fluoride; Department of Atomic Energy has issued sanctions for establishment of 2 units for recovery of uranium from rock phosphatic sources and these are; Rashtriya Chemicals & Fertilizers, Mumbai in association with Heavy Water Board (HWB); and SPIC, Thoothukudi in association with IREL.

RCF is also setting up a rapidwall plant for manufacture of unique building material using phosphogypsum as a raw material which is the by-product of phosphoric acid plant. The project is estimated to cost ₹ 75 crore.

Red phosphorus is manufactured mainly by United Phosphorus Ltd. Red phosphorus is consumed in Matches Industry. It has also applications as fumigant in Agriculture Industry and as flame retardant.

## Joint Ventures Abroad

India's dependency on import at present is to the extent of 25% of our requirements of Urea, 90% in case of phosphates either as raw material or finished fertilizers (DAP/MAP/TSP) and 100% in case of potash. The Government has been encouraging Indian companies to establish joint venture in those countries which are rich in fertilizer resources with arrangements of production facility and to enter into long term agreement for supplying fertilizer to India. In previous years, Department of Fertilizer has undertaken joint

ventures abroad with 5 countries. The details of joint venture project are given below:

(1) IFFCO has joint venture with ICS Senegal in Senegal for the production of 5.50 lakh tonnes of phosphoric acid per year. Production has already started.

(2) A joint venture was made between Oman Oil Co. (OOC-50%), IFFCO (25%) & KRIBHCO (25%) for 16.52 lakh MT Urea and 2.48 lakh MT Ammonia. Production started in the year 2006.

(3) IFFCO and Jordan Phosphate Mining Company (JPMC) have set up a phosphoric acid plant in Jordan of 4.8 lakh tonnes capacity. Commercial production started in December, 2014.

(4) IMACID, a joint venture between Office Cherifien Des Phosphates (OCP), Morocco, Chambal Fertilizers & Chemicals Ltd (CFCL) & TCL (33% each) to produce 4.25 lakh tonnes phosphoric acid production started in 1997-98.

(5) Gujarat State Fertilizers and Chemicals Ltd (GSFC) and Coromandel Fertilizers Limited (CFL) now Coromandel International Limited (CIL) along with Tunisian company 'Group Chimique Tunisien' (GCT) and 'Compagine Des Phosphates De Gafsa' (CPG) are setting up a joint venture company in the name of Tunisia-India fertilizer company (TIFERT), for production of 3.6 lakh tpy phosphoric acid. The entire production of phosphoric acid is for off take by GSFC and CFL. The production started in April, 2014.

Apart from above, the prospects of cooperation with countries like Ghana, Indonesia, Nigeria, Syria, Togo, Canada, etc. too have gained traction.

## ENVIRONMENTAL CONCERNS

There are apparent concerns regarding phospho-gypsum which is formed as a by-product during manufacturing of phosphoric acid. It contains about

1%  $P_2O_5$ , 1% F and 10-30 times more radon, none of which is desirable. Environment Protection Agency (EPA) of USA stipulated in 1989 that phospho-gypsum is unsuitable for sale as common gypsum. Production of each tonne of  $P_2O_5$  yields about five tonnes of phospho-gypsum. EPA has prescribed stringent measures for storage, transport and disposal of phospho-gypsum. In India, however, by-product phospho-gypsum is used widely in cement manufacture.

The use of phosphate also falls under scrutiny. Much attention has been paid to its role in stimulating the growth of algae and other organisms in surface water, the process known as eutrophication. This process is deleterious because it causes blooms of algae which consume dissolved oxygen in lakes and even in shallow, isolated arms of the ocean. Phosphate fertilizers are probably not the only cause of phosphate-induced eutrophication. Another concern is fertilizer phosphate does not leach readily from soil. One of the best ways to remove this phosphate is through the addition of lime which causes precipitation of apatite. However, this procedure, being relatively costly, has not been applied widely. Other application where the use of phosphate has been discouraged is in manufacturing of detergents.

## USES

Most of the phosphate rock mined throughout the world is used to produce phosphate fertilizer. It is also used as animal feed supplements. Elemental phosphorus and phosphoric chemicals derived from phosphate rocks find application in detergents, insecticides, pharmaceutical products, soft drink, tooth paste, glass, photographic films, matches, fire works, military smoke screens, incendiary bombs, etc.

Transparent specimens of apatite with vivid green, blue, yellow or pink colour and excellent clarity are often cut into faceted gemstone.

## SPECIFICATIONS

### Elemental Phosphorus and Phosphoric Acid

BIS (IS:11224-1985, reaffirmed 2010) has prescribed the following specifications of rock phosphate required for the manufacture of elemental phosphorus (Type-I) and phosphoric acid (Type-II).

Sl. No.	Characteristics	Requirement (%)	
		Type I	Type II
1.	Total Phosphate (as P <sub>2</sub> O <sub>5</sub> ) by mass (min.)	30.0	32.0
2.	Silica (as SiO <sub>2</sub> ) % by mass (min.)	10.0	5.0
3.	CO <sub>2</sub> % by mass (max.)	2.0	3.0
4.	Fluoride (F) % by mass (max.)	2.0	4.0
5.	Mixed Aluminium and iron oxide (Al <sub>2</sub> O <sub>3</sub> and Fe <sub>2</sub> O <sub>3</sub> ) % by mass (max.)	3.0	3.5
6.	Moisture % by mass (max.)	1.5	1.5
7.	Magnesium oxide (MgO) % by mass (max.)	0.5	0.5
8.	Chloride (Cl) % by mass (max.)	0.015	0.05
9.	Organic Matter and combined water % by mass (max.)	2.0	1.5

### Single Superphosphate

The P<sub>2</sub>O<sub>5</sub> content in rock phosphate for manufacturing single superphosphate should be minimum 31%. Silica up to 8% can be tolerated. Iron and alumina, i.e., R<sub>2</sub>O<sub>3</sub> should not be more than 3.5%. Higher R<sub>2</sub>O<sub>3</sub> may tend reversion of available P<sub>2</sub>O<sub>5</sub> (water soluble P<sub>2</sub>O<sub>5</sub>). Carbonate up to 5% will improve the reactivity of rock phosphate by increasing the reaction temperature and making the mass porous.

### Direct Application of Rock Phosphate as Fertilizer

In India, the finely-ground rock phosphate containing 16% P<sub>2</sub>O<sub>5</sub> is used for direct application to the soil for soil amendment. This application is dependent upon the structure and chemical composition

of the rock. Direct application is suited mostly for pastures and forage crops and for acidic soils. According to PPCL the following specifications are considered for utilising any rock phosphate as phosphatic fertilizer for direct application in acidic soils.

1.	Absolute citrate solubility index	7% (max.)
2.	Apatite to carbonate ratio CO <sub>2</sub> % : P <sub>2</sub> O <sub>5</sub> %	0.035
3.	Origin of rock phosphate	Sedimentary
4.	Mesh size	100
5.	Hydroxyl ion in crystal lattice is higher indicating substitution of OH for PO <sub>4</sub> :H <sub>2</sub> O	2
6.	Grade of rock phosphate powder citrate soluble fraction	16% P <sub>2</sub> O <sub>5</sub>
7.	Iron as Fe <sub>2</sub> O <sub>3</sub>	5%
8.	CaO to P <sub>2</sub> O <sub>5</sub> ratio	1.8

The use of rock phosphate for direct application as fertilizer depends on its level of solubility in acidic soil.

## CONSUMPTION

The consumption of apatite and rock phosphate in 2015-16 was about 4.36 million tonnes as against 4.34 million tonnes in 2014-15. Fertilizer Industry alone accounted for about 82% consumption followed by Chemical (18%). The consumption of meagre quantities was reported by Glass, Sugar and Iron & Steel Industries as well (Table - 12).

**Table-12: Consumption\* of Apatite and Rock Phosphate, 2013-14 to 2015-16 (By Industries)**

Industry	(In tonnes)		
	2013-14	2014-15 (R)	2015-16 (P)
<b>All Industries</b>	<b>4237900</b>	<b>4340500</b>	<b>4363100</b>
Chemical	790700	792400	795600
Fertilizer	3446800	3547700	3567100
Others (glass & sugar)	400	400	400

*Figures rounded off.*

*\*Includes actual reported consumption and/or estimates made wherever required.*

*\* Due to paucity of data, the consumption figures may not be completed.*

## POLICY

Imports of natural calcium phosphates (including apatite), natural aluminium-calcium phosphates and phosphatic chalk are allowed 'free' under Heading No. 2510 as per the Foreign Trade Policy 2015-2020. All chemical fertilizers except urea continue to be decontrolled. The Government of India has been implementing a scheme of concession fixing indicative maximum retail price (MRP) for enabling sales of decontrolled phosphatic and potassic fertilizers at reasonable prices.

In case of Phosphate Fertilizer Industry, the scarcity of domestic raw material constrains the attainment of self-sufficiency in the country. A policy has, therefore, been adopted which involves the following three options:

- i) domestic production based on indigenous imported rock phosphate and imported sulphur.
- ii) domestic production based on imported intermediates, viz, phosphoric acid.
- iii) imports of finished fertilizers.

Government of India notified new Urea Policy 2015 for existing gas based urea manufacturing units.

## WORLD REVIEW

The world reserves of phosphate rock are about 68 billion tonnes, located mainly in Morocco & Western Sahara (74%), China (5%), Syria (3%), and other countries which contribute the remaining 18% (Table - 13).

The world production of phosphate rock increased to 265 million tonnes in 2015 from 242 million tonnes in 2014. China (54%), Morocco (10%), USA (10%) and Peru & Russia (4% each) have been the major producers (Table- 14).

### Canada

Fertoz limited continued developing the Fernie and Wapiti phosphate rock deposits in British Columbia and

conducted exploration activities at the Fernie Project in 2015.

In Quebec, two phosphate rock mines receive mining permits from Provincial authorities in 2015. That will be developed by Investment Quebec (62%) and Yara International ASA (Norway) (38%). The proposed openpit mine would produce between 1.2 and 1.5 million tonnes per year of high grade apatite concentrate for about 30 years.

Arianne Phosphate Inc. received permit for its Laca Paul phosphate project in December 2015 and planned to begin production in 2018.

### Morocco

OCP Group continued with an expansion programme that was to increase its mine capacity from 32 million tonnes per year to 55 million tonnes per year during next decade. In 2015, construction was ongoing at the Khourigba and Gantour mining areas. A 10 Mt/yr expansion at Khourigba was planned to be completed in 2016. OCP planned to open new mines at Meskala deposit in the Essaouria Region after 2023.

### Saudi Arabia

Ma'aden Phosphate Co. (MPC) continued development work at the Umm Wu'al Phosphate Mine on the Al-Khabra deposit. The project was to include the phosphate rock mine and beneficiation plant and production facilities for phosphoric acid, animal feed, purified phosphoric acid, sodium tripolyphosphate and sulphuric acid. Proposals to expand the existing fertilizer plants at Ras Al Khair are also part of the project. The production capacities planned are 5.3 million tpy of phosphate concentrate, 1.5 million tpy of phosphoric acid and 3.5 million tpy of phosphate fertilizers. The project was expected to be completed in 2017.

APATITE AND ROCK PHOSPHATE

**Table – 13 : World Reserves of Phosphate Rock (By Principal Countries)**

(In '000 tonnes)

Country	Reserves
<b>World: Total (rounded)</b>	<b>68000000</b>
Algeria	2200000
Australia	1100000
Brazil	320000
China	3100000
Egypt	1200000
India	65000
Israel	130000
Jordan	1200000
Kazakhstan	260000
Mexico	30000
Morocco & Western Sahara	50000000
Peru	820000
Russia	1300000
Saudi Arabia	680000
Senegal	50000
South Africa	1500000
Syria	1800000
Togo	30000
Tunisia	100000
USA	1100000
Vietnam	30000
Other countries	810000

*Source: Mineral Commodity Summaries, 2017.*

## FOREIGN TRADE

### Exports

In 2015-16, exports of rock phosphate was up drastically to 14242 tonnes from 437 tonnes achieved in the previous year. Exports of phosphatic fertilizers at 15,510 tonnes in 2015-16 increased drastically from 2,081 tonnes recorded in the preceding year. The exports of phosphoric acid increased considerably to 14,955 tonnes from 4,014 tonnes and that of elemental phosphorus to 486 tonnes from 360 tonnes in the previous year. Rock phosphate was exported mainly to Malayasia (59%). Elemental phosphorus was mainly exported to USA (22%). In 2015-16, exports of phosphatic fertilizers were almost to Nepal (28%) and Pakistan (72%) while phosphoric acid was mainly exported to Bangladesh (65%) (Tables- 15 to 20).

**Table – 14 : World Production of Phosphate Rock (By Principal Countries)**

(In '000 tonnes)

Country	2013	2014	2015
<b>World: Total</b>	<b>238001</b>	<b>241933</b>	<b>265140</b>
Algeria	1150	1127	1150 <sup>e</sup>
Australia	2064	1950	1028
Brazil	6715	6513	5600
China	108510	120438	142039
Egypt	5922	5500	5500
India	1454	1607	1474
Israel	2539	2779	3427
Jordan	5399	7144	8336
Kazakhstan	1832	1830 <sup>e</sup>	1830 <sup>e</sup>
Morocco	26400	27390	26264
Mexico	2217	1663	1677
Peru	14842	10884	11162
Russia	10500	10700	10700 <sup>e</sup>
Saudi Arabia	1820	1911	2002
South Africa	2132	2011	1852
Togo	1214	1086	1150
Tunisia	3284	3784	3800 <sup>e</sup>
USA	31200	25300	27600 <sup>e</sup>
Vietnam	2656	2471	2758
Other countries	6151	5845	5792

*Source: World Mineral Production, 2011-2015.*

### Imports

Imports of rock phosphate decreased slightly to 8.03 million tonnes in 2015-16 from 8.27 million tonnes in the previous year. Imports were mainly from Jordan (39%), Egypt (22%) and Morocco (17%). Imports of elemental phosphorus decreased marginally to 24,530 tonnes in 2015-16 from 24,858 tonnes in the previous year. The imports of elemental phosphorus were mainly from Vietnam (88%). During 2015-16, 145 tonnes of phosphatic fertilizers were imported mainly from China (85%). Imports of phosphoric acid increased marginally to 2.19 million tonnes in 2015-16 from 1.80 million tonnes in the previous year. Imports were mainly from Morocco (47%), Jordan (14%) and Senegal (11%) (Tables- 21 to 26).

APATITE AND ROCK PHOSPHATE

**Table – 15 : Exports of Rock Phosphate  
(By Countries)**

Country	2014-15		2015-16 (P)	
	Qty (t)	Value (` '000)	Qty (t)	Value (` '000)
<b>All Countries</b>	<b>437</b>	<b>2916</b>	<b>14242</b>	<b>69096</b>
Malayasia	-	-	8381	38400
Bhutan	-	-	1856	14936
UAE	417	2232	3203	13971
Nepal	6	186	799	1392
Germany	-	-	++	218
Tanzania	-	-	1	106
Kenya	5	28	2	73
Congo	6	247	-	-
Canada	2	115	-	-
Sri Lanka	1	108	-	-

**Table – 16 : Exports of Rock Phosphate  
(Ground)  
(By Countries)**

Country	2014-15		2015-16 (P)	
	Qty (t)	Value (` '000)	Qty (t)	Value (` '000)
<b>All Countries</b>	<b>419</b>	<b>2352</b>	<b>14200</b>	<b>68461</b>
Malayasia	-	-	8381	38400
Bhutan	-	-	1856	14936
UAE	417	2232	3202	13951
Nepal	2	114	758	995
Tanzania	-	-	1	106
Kenya	++	6	2	72

**Table – 18 : Exports of Phosphorus (Elemental)  
(By Countries)**

Country	2014-15		2015-16 (P)	
	Qty (t)	Value (` '000)	Qty (t)	Value (` '000)
<b>All Countries</b>	<b>360</b>	<b>129957</b>	<b>486</b>	<b>178268</b>
USA	78	25056	105	34787
Indonesia	48	18709	52	21130
South Africa	42	16236	42	17491
Philippines	16	5702	40	14712
Canada	-	-	42	13926
Brazil	15	6206	31	11890
Egypt	1	387	28	11193
Slovenia	-	-	20	8153
Hungary	40	14520	20	7738
Iran	31	14328	25	6082
Other countries	89	28813	81	31166

**Table – 17 : Exports of Rock Phosphate  
(Unground)  
(By Countries)**

Country	2014-15		2015-16 (P)	
	Qty (t)	Value (` '000)	Qty (t)	Value (` '000)
<b>All Countries</b>	<b>18</b>	<b>564</b>	<b>42</b>	<b>635</b>
Nepal	4	72	41	397
Germany	-	-	++	218
UAE	-	-	1	20
Congo, D. Rep.	6	247	-	-
Canada	2	115	-	-
Sri Lanka	1	108	-	-
Kenya	5	21	-	-
Mauritius	++	1	-	-

**Table – 19 : Exports of Phosphatic Fertilizers  
(By Countries)**

Country	2014-15		2015-16 (P)	
	Qty (t)	Value (` '000)	Qty (t)	Value (` '000)
<b>All Countries</b>	<b>2081</b>	<b>24053</b>	<b>15510</b>	<b>390524</b>
Nepal	2080	22735	4267	292972
Pakistan	-	-	11228	97172
Greece	-	-	++	200
Malaysia	1	80	1	160
Mauritius	-	-	14	19
Central African Republic	++	407	-	-
Germany	++	683	-	-
Ghana	++	147	-	-
Trinidad	++	1	++	1

**Table – 20 : Exports of Phosphoric Acid  
(By Countries)**

Country	2014-15		2015-16 (P)	
	Qty (t)	Value (` '000)	Qty (t)	Value (` '000)
<b>All Countries</b>	<b>4014</b>	<b>110979</b>	<b>14955</b>	<b>412100</b>
Bangladesh	5	597	9827	265445
Korea, Rep. of	3877	88951	5001	128695
UAE	26	4595	23	4559
Mozambique	22	2821	31	4320
Belgium	19	4928	12	2772
Nepal	35	2656	22	1609
Sri Lanka	11	2580	6	1277
Taiwan	3	430	6	928
Ethiopia	++	70	3	573
Tanzania	++	7	3	488
Other countries	16	3344	21	1434

APATITE AND ROCK PHOSPHATE

**Table – 21 : Imports of Rock Phosphate  
(By Countries)**

Country	2014-15		2015-16 (P)	
	Qty (t)	Value (` '000)	Qty (t)	Value (` '000)
<b>All Countries</b>	<b>8273261</b>	<b>61888711</b>	<b>8037745</b>	<b>65290421</b>
Jordan	3207260	24952331	3157242	26448984
Morocco	1281538	10429359	1395306	13818387
Egypt	1788548	10244485	1761293	10215106
Peru	849506	5677888	889315	6943142
Togo	805367	7717209	461315	5051994
Algeria	62615	450441	217900	1619172
Israel	171298	1381560	98161	715117
Senegal	32396	222261	33000	250361
South Africa	21122	185852	22000	198165
Pakistan	189	3450	771	18918
Other countries	53422	623875	1442	11075

**Table – 22 : Imports of Rock Phosphate  
(Ground)  
(By Countries)**

Country	2014-15		2015-16 (P)	
	Qty (t)	Value (` '000)	Qty (t)	Value (` '000)
<b>All Countries</b>	<b>3338527</b>	<b>25563139</b>	<b>3027109</b>	<b>26564902</b>
Morocco	1175827	9487032	1395306	13818387
Egypt	993869	5785890	672366	4008921
Togo	470154	4572132	356114	3876138
Jordan	452764	3527196	442908	3632324
Israel	171298	1381560	98161	715117
Senegal	-	-	33000	250361
South Africa	21122	185852	22000	198165
Algeria	-	-	5585	42196
Pakistan	189	3450	579	14003
UAE	-	-	500	4472
Other countries	53304	620027	590	4818

**Table – 23 : Imports of Rock Phosphate  
(Unground)  
(By Countries)**

Country	2014-15		2015-16 (P)	
	Qty (t)	Value (` '000)	Qty (t)	Value (` '000)
<b>All Countries</b>	<b>4934734</b>	<b>36325572</b>	<b>5010636</b>	<b>38725519</b>
Jordan	2754496	21425135	2714334	22816660
Peru	849506	5677888	889315	6943142
Egypt	794679	4458595	1088927	6206185
Algeria	62615	450441	212315	1576976
Togo	335213	3145077	105201	1175856
Pakistan	-	-	192	4915
France	18	667	18	703
Bangladesh	-	-	296	486
Finland	-	-	1	226
China	100	3179	15	179
Other countries	138107	1164590	22	191

**Table – 24 : Imports of Phosphorus  
(Elemental)  
(By Countries)**

Country	2014-15		2015-16 (P)	
	Qty (t)	Value (` '000)	Qty (t)	Value (` '000)
<b>All Countries</b>	<b>24858</b>	<b>4798749</b>	<b>24530</b>	<b>4658199</b>
Vietnam	24323	4693281	21612	4124035
China	535	105383	2918	534098
USA	++	21	++	30
UK	-	-	++	17
Belgium	-	-	++	15
Germany	++	10	++	4
Netherlands	++	54	-	-
Other countries	-	-	-	-



**Table – 25 : Imports of Phosphoric Acid  
(By Countries)**

Country	2014-15		2015-16 (P)	
	Qty (t)	Value (` '000)	Qty (t)	Value (` '000)
<b>All Countries</b>	<b>1798213</b>	<b>83022269</b>	<b>2192097</b>	<b>109650505</b>
Morocco	937614	43137203	1034663	52582287
Jordan	152594	7340491	317830	16505037
Senegal	153799	6940199	247142	12812978
USA	236112	10860028	178087	9374620
Tunisia	192767	8700262	127674	6083673
Vietnam	23866	1081525	107163	4769258
Israel	50207	2382636	60815	3108333
South Africa	25212	1113178	61952	2234983
Saudi Arabia	-	-	31278	781865
Chinese Taipei/ Taiwan	8791	423023	11549	518911
Other countries	17251	1043724	13944	878560

## FUTURE OUTLOOK

There is no substitute for phosphorus in agriculture. The country is deficient in all fertilizer minerals. The reserves/resources of chemical and fertilizer grades apatite and rock phosphate in India are very limited. Therefore, detailed exploration is necessary for conversion of remaining resources into reserves. Secondly, the search for apatite and rock phosphate may have to be intensified in Andhra Pradesh, Rajasthan, Madhya Pradesh, Jharkhand, Tamil Nadu, Meghalaya, Gujarat, Uttar Pradesh, Uttarakhand, West Bengal, etc. Till the domestic resources of these two minerals are improved, the country has no alternative but to depend on imports. Concerted efforts should be made by way of constituting consortia of public private companies to acquire assets abroad specifically in countries like Uzbekistan, Jordan, etc. Strengthening ties with mineral-rich countries and provinces with functional and specific MoUs and utilisation of IMG mechanism to align domestic stakeholders with MoUs is required. Only about 10-15% requirement of raw material for phosphate fertilizer production is met through indigenous sources. The remaining requirement is met through import in the form of rock phosphate, phosphoric acid and direct fertilizers. Private Sector participation in rock phosphate

**Table – 26 : Imports of Phosphatic Fertilizers  
(By Countries)**

Country	2014-15		2015-16 (P)	
	Qty (t)	Value (` '000)	Qty (t)	Value (` '000)
<b>All Countries</b>	<b>110</b>	<b>6369</b>	<b>145</b>	<b>8950</b>
China	100	5068	123	6289
Turkey	7	1230	5	1618
Australia	-	-	17	842
France	-	-	++	86
Spain	-	--	++	66
Italy	-	-	++	49
USA	3	71	-	-
Other countries	-	-	-	-

mining needs to be promoted in order to make available the above two minerals to reduce import dependence for promotion of fertilizers for Agricultural Sector.

Demand of phosphatic fertilizer is expected to increase gradually in tandem with the growth in population and corresponding increase in food requirements. The government has been encouraging Indian companies to establish joint venture abroad in countries which are rich in fertilizer resources.

In India, most of the existing phosphatic fertilizer and phosphoric acid plants have been designed for high-grade imported rock phosphate, mainly from Morocco and Jordan. The Indian deposits on the other hand, are of low-grade variety. Therefore, the fertilizer and phosphoric acid plants that are likely to be set up as replacement of the existing plants may have to be designed to accept indigenous ores as feed. In addition, beneficiation of domestic low-grade ores would be a step in the right direction and should be promoted persuasively.

The Working Group has made a series of recommendations which included: (i) Mining of rock phosphate be opened for Private Sector, (ii) Cluster mining be encouraged in order to reduce mining loss and degradation of environment to the maximum extent possible, (iii) Environmental issues be sought amicably for commencement of mining operations in Aravali areas, (iv) Technology for extraction of low-grade ores be adopted and (v) Expand exploration to various other parts of the country.