

MOLYBDENUM



Indian Minerals Yearbook 2018

(Part- II : Metals & Alloys)

57th Edition

MOLYBDENUM

(FINAL RELEASE)

**GOVERNMENT OF INDIA
MINISTRY OF MINES
INDIAN BUREAU OF MINES**

Indira Bhavan, Civil Lines,
NAGPUR – 440 001

PHONE/FAX NO. (0712) 2565471
PBX : (0712) 2562649, 2560544, 2560648
E-MAIL : cme@ibm.gov.in
Website: www.ibm.gov.in

June, 2019

11 Molybdenum

Molybdenum (Mo) is a refractory metal used principally as an alloying agent in steel, cast iron & superalloys to enhance strength and resistivity to wear & corrosion. It does not occur in nature in free state. Usually, it is found in chemically combined form with other elements. Molybdenite (MoS_2) is the principal ore of molybdenum. About two-thirds of global molybdenum production is as by-product of copper mining and only about one-third is obtained from primary molybdenum mines. In India, by-product concentrates of molybdenum are produced intermittently from uranium ore of Jaduguda mine belonging to Uranium Corporation of India Ltd (UCIL) in Jharkhand. The internal demand for molybdenum and its products is met mostly through imports.

RESERVES/RESOURCES

India though is endowed with rich mineral wealth, there are several critical minerals that it lacks and one of them is molybdenum. In India, molybdenum is associated generally with copper, lead and zinc ores. Rakha copper deposit in Jharkhand contains 45 to 48 ppm molybdenum. Malanjkhand copper deposit in Madhya Pradesh contains 0.04% recoverable molybdenum. Dariba-Rajpura lead-zinc deposit in Rajasthan contains molybdenum besides bismuth, arsenic and cadmium. The multimetal deposit at Umpyrtha in Khasi and Jaintia Hills, Meghalaya, reportedly contains molybdenum in association with copper, lead and tungsten. Molybdenum deposit in Karadikuttam in Madurai district, Tamil Nadu, contains 0.02 to 0.14% recoverable molybdenum.

As per NMI database as on 1.4.2015, based on UNFC System, the resources of molybdenum ore in the country have been estimated at 19.37 million tonnes containing about 12,668 tonnes MoS_2 . The above resources of ore are located in Tamil Nadu (10 million tonnes), Madhya Pradesh (8 million tonnes) and Karnataka (1.32 million tonnes) (Table1).

EXPLORATION & DEVELOPMENT

The exploration and development details if any are covered in the Review on "Exploration & Development" in "General Reviews" Vol.I of the title.

USES

Molybdenum is a versatile alloying agent for alloy steel, cast iron, nickel, cobalt and titanium alloys. For desired metallurgical properties, it is used in the form of molybdic oxide or ferro-molybdenum. It is used in different proportions for imparting desired properties, such as, increased strength, hardness and resistance to corrosion, temperature and chipping. It also finds application in permanent magnet alloys. As a refractory metal, it is used in many electrical and electronic components and as resistance element in electric furnaces and other equipment which are operated at extremely high temperatures. Its non-metallurgical uses are in lubricants, catalysts, pigments, as an additive in oil and greases, in aerosol sprays, in reducing surface friction and as an antiwear and antifriction agent in plastics. Molybdenum plays a vital role in the Energy Industry and it may become an increasingly essential factor in green technology.

SUBSTITUTES

There is hardly any substitution for molybdenum in its major application, viz, as an alloying element in steel and cast irons. Owing to the non-availability of molybdenum, there was an apparent need to develop new materials that could be a suitable substitute vis-à-vis the alloying properties of the metal. Potential substitutes for molybdenum include chromium, vanadium, niobium (columbium) and boron in alloy steels; tungsten in tool steels; graphite, tungsten and tantalum for refractory materials in high temperature electric furnaces and chrome-orange, cadmium-red and organic-orange pigments for molybdenum orange.

MOLYBDENUM

**Table – 1 : Reserves/Resources of Molybdenum as on 1.4.2015
(By Grades/States)**

(In tonnes)

Grade/State	Reserves		Remaining Resources					Total Resources (A+B)
	Total (A)	Pre-feasibility STD221	Measured STD331	Indicated STD332	Inferred STD333	Reconnaissance STD334	Total (B)	
All India : Total								
Ore	-	1500000	36000	569304	17098594	167800	19371698	19371698
Contained MoS₂	-	1050	83	287	11198.03	50.34	12668.37	12668.37
By States								
Karnataka								
Ore	-	-	-	-	1320900	-	1320900	1320900
Contained MoS ₂	-	-	-	-	1718.7	-	1718.7	1718.7
Madhya Pradesh								
Ore	-	-	-	-	8000000	-	8000000	8000000
Contained MoS ₂	-	-	-	-	5020	-	5020	5020
Tamil Nadu								
Ore	-	1500000	36000	569304	7777694	167800	10050798	10050798
Contained MoS ₂	-	1050	83	287	4459.33	50.34	5929.67	5929.67

Figures rounded off.

INDUSTRY AND CONSUMPTION

Usually, molybdenum is used in the form of roasted concentrates, oxide or ferro-molybdenum in the defence industries. The production of ferro-molybdenum decreased from 1,603 tonnes in 2016-17 to 1,205 tonnes in 2017-18 (Table-2). Consumption of ferro-molybdenum for the years 2013-14 to 2015-16 (by Industries) is furnished in Table-3. Alloy steel industry alone accounted for about 66% consumption followed by iron & steel (29%) and foundry (4%). Non-ferrous Technology Development Centre at the Defence Metallurgical Research Laboratory, Hyderabad, has a pilot plant for producing molybdenum powder. Institute of Minerals and Materials Technology (formerly RRL), Bhubaneswar, has been undertaking basic research on recovery of molybdenum from spent catalysts.

**Table – 2 : Production of Ferro-molybdenum
2013-14 to 2017-18**

(In tonnes)	
Year	Production
2013-14	1231
2014-15	1295
2015-16	1459
2016-17	1603
2017-18 (P)	1205

Source: Monthly Statistics of Mineral Production, February 2018, IBM.

**Table – 3 : Consumption* of
Ferro-molybdenum, 2013-14 to 2015-16
(By Industries)**

(In tonnes)			
Industry	2013-14	2014-15	2015-16 (P)
All Industries	672	708	1449
Alloy steel	435	472	950
Electrode	20	17	17
Foundry	57	59	59
Iron & steel	160	160	423

(* Includes actual reported consumption and/or estimates made wherever required and due to paucity of data, coverage may not be completed).

Moly Metal LLP, a leading manufacturer of Molybdenum alloys-ferro molybdenum (FeMo) and molybdenum disulphide (MoS₂) commenced production in 2007 at a new manufacturing plant in the U.T. of Daman. RUBAMIN, a Gujarat based company, reportedly has a capacity of 1,500 tonnes per annum sodium molybdate and 800 tonnes per annum ammonium molybdate both of which are derivatives of molybdenum.

TRADE POLICY

As per Foreign Trade Policy, 2015-2020, imports of molybdenum ores & concentrates under Exim code 2613 and molybdenum & articles thereof under Exim code 8102 are allowed free, except molybdenum waste & scrap (under ITC-HS Code No. 8102 9700) which are restricted.

WORLD REVIEW

The world reserves of molybdenum are 17 million tonnes, located mainly in China (49%), USA (16%), Peru (14%), Chile (8%) and Russia (6%) (Table-4).

**Table– 4: World Reserves of Molybdenum
(By Principal Countries)**

(In '000 tonnes of molybdenum content)	
Country	Reserves
World: Total (rounded)	17000
Armenia	150
Argentina	100
Canada	100
Chile	1400
China ^(e)	8300
Iran	43
Mexico	130
Mongolia	210
Peru	2400
Russia ^(e)	1000
Turkey	700
USA	2700
Uzbekistan ^(e)	60

Source: Mineral Commodity Summaries, 2019.

MOLYBDENUM

**Table – 5 : World Mine Production of Molybdenum
(By Principal Countries)**

(In tonnes of metal content)

Country	2015	2016	2017
World: Total (rounded)	289665	282209	305244
Armenia	5324	5438	5590
Canada	1983	2883	5306
Chile	52398	55834	62454
China	135270	129357	130000 ^e
Iran	6705	6975	7000 ^e
Mexico	11327	11896	13985
Mongolia	2557	2431	2639
Peru	20153	25757	28141
Russia	3254	3359	2806
USA	47400	35800	44600
Other countries	3294	2479	2723

*Source: World Mineral Production, 2013-17, BGS.
e:- Estimated*

The world mine production of molybdenum in terms of metal content increased to 3.05 lakh tonnes in 2017 from 2.82 lakh tonnes in 2016. China with 43% production was the main producer of molybdenum in the world followed by Chile (20%), USA (15%), Peru (9%) and Mexico (5%) in 2017 (Table-5).

To give a generalised view of the development in various countries the country wise description is sourced from available publication Mineral Yearbook of USGS 2016 is furnished below.

Canada

Teck Resources Ltd announced that its Highland Valley Mine in south-central British Columbia produced 3,490 tonnes of molybdenum concentrate in 2016, a 75% increase from the 2,000 tonnes of molybdenum concentrate produced in 2015. The Company attributed the large increase to higher grade of ore. The Company targetted molybdenum production was expected to be approximately 4,100 to 4,300 tonnes/year in 2017, before declining to approximately 3,200 tonnes/year from 2018 to 2020.

At its Gibraltar Mine in south-central British Columbia, Taseko Mines Ltd produced 430 tonnes of molybdenum in 2016, a slight decrease from the 437 tonnes of molybdenum produced in 2015.

The molybdenum circuit at Gibraltar restarted in September 2016 after being idle since the third quarter of 2015.

Chile

In 2015, Amerigo Resources Ltd produced only 44 tonnes of molybdenum at its Minera Valle Central processing facility in central Chile because molybdenum was only produced in the first quarter of 2015. Molybdenum production restarted in August 2016, with an annual production of 230 tonnes of molybdenum.

Antofagasta plc announced that the by-product molybdenum production at its Los Pelambres Mine in 2016 was 7,100 tonnes, the production showed a decline of 30% when compared to 10,100 tonnes of molybdenum produced in 2015. Antofagasta also announced that it was constructing a new molybdenum plant at Centinela.

MOLYBDENUM

The new plant was expected to produce approximately 2,400 tonnes/year of molybdenum concentrate, and construction was expected to commence in 2017.

Corporación Nacional del Cobre de Chile (CODELCO), the state-controlled copper and molybdenum producer, announced that it produced 30,600 tonnes of molybdenum in 2016 as against 27,700 tonnes in 2015. CODELCO attributed the 10% increase in molybdenum production to higher output from the Chuquicamata open pit mine.

The Sierra Gorda project, in the Antofagasta Region in northern Chile, was a Joint Venture among KGHM International Ltd, Sumitomo Metal Mining Co., Ltd, and Sumitomo Corp. under the company Sierra GordaSCM.

The Sierra Gorda Mine produced 10,000 tonnes of molybdenum concentrate in 2016, a 52% increase when compared to the 6,600 tonnes of molybdenum concentrate produced in 2015. The increase was mainly attributed to the mine and processing plant remaining in the rampup phase during the first half of 2015.

Argentina

Minera Alumbraera Ltd began molybdenum production at the Alumbraera copper-gold-molybdenum mine in northern Argentina in 2008 when it commissioned a molybdenum recovery circuit. The Alumbraera Mine is a Joint Venture among Glencore plc (50%), Goldcorp Inc. (37.5%) and Yamana Gold Inc. (12.5%). According to the Company, all molybdenum produced from the mine was exported to Chile.

Mexico

Grupo Mexico S.A.B. de C.V. (Grupo Mexico) reported that its La Caridad Mine, in northeastern Sonora, produced 9,900 tonnes of molybdenum concentrate in 2016 as compared to 10,040 tonnes of molybdenum concentrate produced in 2015. Grupo Mexico also reported that it completed the \$3.5 billion investment programme at Buenavista del Cobre on time and \$100 million below budget. The new copper-molybdenum concentrator has a production capacity

of 1,88,000 tonnes/year of copper and 2,600 tonnes/year of molybdenum concentrate. In 2016, it produced 1,600 tonnes of molybdenum concentrate. The Buenavista Mine is located 40 km south of the border between the United States (Arizona) and Mexico.

Peru

The Cerro Verde Mine (FCX has a 53.56% ownership interest) is an open pit copper and molybdenum mining complex, 16 km southwest of Arequipa. According to FCX, the Cerro Verde expansion project commenced operations in September 2015 and achieved capacity operating rates during the first quarter of 2016. Production in 2016 was approximately 9,500 tonnes of molybdenum concentrate as against 3,200 tonnes of molybdenum concentrate produced in 2015.

Grupo Mexico also announced that it continued to work on the Toquepala expansion project in southern Peru. The Toquepala expansion project was expected to increase annual molybdenum production by 3,100 tonnes. The project was expected to be complete in the second quarter of 2018.

Chinalco Mining Corporation International announced that, as of June 2016, the molybdenum hydrometallurgical project at the Toromocho copper-molybdenum operation had not started production. The Toromocho project is located in central Peru in the core of the Morochocha mining district. The molybdenum operation had a production capacity of 25.1 t/d of molybdenum over the life of the mill and would be Peru's first molybdenum-processing facility.

China

Chinese molybdenum production took place predominantly in Hebei, Henan, and Shaanxi Provinces and Nei Mongol Autonomous Region. China has a large number of small-scale mining operations that were very susceptible to changes in prices and also were able to increase or decrease production quickly during price fluctuations. In 2016, the decrease in Chinese production was attributed to a new round of environmental inspections that was launched by the Chinese Government.

MOLYBDENUM

The environmental inspections have forced some producers to shut down permanently or upgrade their facilities to comply with stricter environmental standards. Jinduicheng Molybdenum Co. Ltd announced that it reduced production in 2016. Inner Mongolia Zhongxi Mining Co. Ltd announced that their 2016 production levels remained unchanged.

Armenia

The Zangezur Copper-Molybdenum Combine continued to produce molybdenum is at Kajaran Mine. According to Cronimet Mining AG, the Kajaran Mine is the leading copper and molybdenum mine in Armenia. Zangezur Copper-Molybdenum shareholders are Cronimet Mining (60%), Pure Iron Plant OJSC (15%), Armenian Molybdenum Production Ltd. (12.5%), and Zangezur Mining Ltd. (12.5%).

In 2016, Vallex Group (Yerevan) completed the construction of its copper and molybdenum ore processing plant near the Kashen deposit and started processing its first ore. The deposit contained an estimated 56 Mt of ore with 0.49% copper content and 0.006% molybdenum content. Vallex has been working on the Kashen Mine since 2012 and has invested approximately \$120 million to bring it to the first phase of production. Vallex also owns the Teghut copper and molybdenum mine and concentrator plant located in the Tumanyan region in northern Armenia. According to the company, the Teghut Mine has been producing approximately 380 tonnes/year of molybdenum concentrate.

FOREIGN TRADE

Exports

Exports of molybdenum ores & concentrates decreased sharply by 68% to 7 tonnes in 2017-18 from 22 tonnes in 2016-17. Exports were mainly to Oman (71%) & UAE (29%). Exports of molybdenum and scrap increased manifold to 292 tonnes in 2017-18 from 12 tonnes in 2016-17. Exports were mainly to Netherlands (74%) & Germany (24%) (Tables-6 & 7).

Imports

Imports of molybdenum ores & concentrates increased slightly to 9,169 tonnes in 2017-18 from 7,139 tonnes in 2016-17. Imports were mainly from Chile (36%), Thailand (24%), USA (9%), Korea, Rep. of & Netherlands (8% each), Iran (4%) and Mexico (3%). Imports of molybdenum and scrap decreased marginally to 393 tonnes in 2017-18 from 398 tonnes in the 2016-17. Imports were mainly from China (67%), Austria (22%), USA (6%) and UK (2%) (Tables-8 & 9).

Table – 6 : Exports of Molybdenum Ores & Conc. (By Countries)

Country	2016-17		2017-18	
	Qty (t)	Value (` '000)	Qty (t)	Value (` '000)
All Countries	22	1005	7	1922
UAE	-	-	2	891
Egypt	-	-	++	770
Oman	22	1004	5	261
UK	++	1	-	-

Table – 7 : Exports of Molybdenum & Scrap (By Countries)

Country	2016-17		2017-18	
	Qty (t)	Value (` '000)	Qty (t)	Value (` '000)
All Countries	12	143814	292	180111
Netherlands	-	-	215	46901
Germany	1	32032	69	34388
Austria	1	9165	2	16719
Italy	++	10524	++	11205
Japan	1	26325	++	10333
USA	1	11165	1	10256
China	++	1905	++	8801
Poland	1	7179	1	8654
Singapore	++	9076	++	7467
Egypt	++	3747	1	3600
Other countries	7	32696	3	21787

MOLYBDENUM

**Table – 8 : Imports of Molybdenum Ores and Conc.
(By Countries)**

Country	2016-17		2017-18	
	Qty (t)	Value (` '000)	Qty (t)	Value (` '000)
All Countries	7139	5442499	9169	8149457
Chile	2274	1748715	3298	2667607
Thailand	1541	1323969	2211	2423961
Mexico	910	605988	304	248497
USA	578	399108	830	638918
Korea, Rep. of	513	345157	760	595367
Netherlands	421	375147	693	639758
Iran	254	252403	409	485872
Belgium	245	190455	88	72461
Vietnam	94	47753	100	72122
China	90	76895	114	123425
Other countries	219	76909	362	181469

**Table –9 : Imports of Molybdenum & Scrap
(By Countries)**

Country	2016-17		2017-18	
	Qty (t)	Value (` '000)	Qty (t)	Value (` '000)
All Countries	398	1104069	393	1197143
China	294	724047	265	664097
Austria	44	208529	86	364799
USA	26	95963	23	82933
France	1	4727	3	30581
Germany	3	17350	5	22165
UK	3	6864	6	11054
Singapore	2	11176	1	8121
Hong Kong	3	12763	1	5467
Canada	++	1684	1	2334
Belgium	1	1417	1	1721
Other countries	21	19549	1	3871

FUTURE OUTLOOK

The principal uses of molybdenum in chemical applications and as catalyst and as an additive in steel manufacturing, most importantly alloy and stainless steel, are expected to continue. Molybdenum plays a vital role in the Energy Industry and it may become increasingly important factor in environment protection technology, where it is used in high strength steels for automobiles to reduce weight and improve fuel economy and safety. Molybdenum-based catalysts have a number of important applications in Petroleum and Plastic Industries.

A major use is in the hydrodesulfurisation of petroleum, petrochemicals and coal-derived liquids. Production of ultra-low-sulphur diesel fuels is expected to more than double the amount of molybdenum used in oil refineries. Molybdenum not only allows for economical fuel refining, it also contributes to a safer environment through lower sulphur emissions. Analysts expect global demand for catalysts to continue to increase as there are no practical alternatives to molybdenum in many of its catalytic applications. The need for companies to reduce carbon dioxide emissions from coal-fired power stations will require plants to run at higher temperatures, resulting in greater demand for higher grade molybdenum-bearing steels.
