

CRYOLITE



Indian Minerals Yearbook 2018

(Part- III : Mineral Reviews)

57th Edition

CRYOLITE

(FINAL RELEASE)

GOVERNMENT OF INDIA
MINISTRY OF MINES
INDIAN BUREAU OF MINES

Indira Bhavan, Civil Lines,
NAGPUR – 440 001

PHONE/FAX NO. (0712) 2565471
PBX : (0712) 2562649, 2560544, 2560648
E-MAIL :cme@ibm.gov.in
Website: www.ibm.gov.in

June, 2019

8 Cryolite

Cryolite is a double fluoride of sodium and aluminium and has a stoichiometry very near the formula Na_3AlF_6 and a melting point of about $1,010^\circ\text{C}$. Its occurrence in substantial quantities was established in Greenland and was mined extensively there in the early twentieth century, but the mine is now essentially exhausted. It is colourless to white but occurs in other shades too, for instance brown, red and some times black. It has a specific gravity of about 2.5 to 3. It has a low index of refraction close to that of water. Synthetic cryolite is used as an electrolyte in the reduction of alumina to aluminium due to non-availability of natural cryolite. Composition and properties of synthetic cryolite are the same as those of natural cryolite, but synthetic cryolite is often deficient in sodium fluoride.

INDUSTRY

Synthetic cryolites are obtained by adopting several processes. The selection of the process depends upon the availability and cost of raw materials. The simplest and most common method of obtaining synthetic cryolite is by reacting hydrofluoric acid with soda ash and alumina hydrate. Hydrofluoric acid is produced by reacting acid grade fluorspar with sulphuric acid and this process also yields gypsum as by-product. In the secondary reaction between hydrofluoric acid and sodium chloride brine, sodium fluoride and hydrochloric acid are produced. In the primary reaction, dry aluminium hydroxide reacts with hydrofluoric acid to produce aluminium fluoride which reacts with sodium fluoride produced earlier and forms synthetic cryolite.

Besides fluorspar, fluorine gas produced as by-product at plants that produces phosphatic fertilizer and phosphoric acid, has emerged as an important alternative source for hydrofluoric acid and other fluorine chemicals including cryolite and aluminium fluoride. Rock phosphate usually contains 7-8% CaF_2 . In terms of fluorine, it works out to 3-4% which is liberated at the time of acidulation of rock phosphate with sulphuric acid.

Fluorine combines with silica to form silicon tetrafluoride which when scrubbed with water forms fluorosilicic acid. By recycling, 18-24% fluorosilicic acid is obtained, which serves as a raw material for manufacturing various fluorochemicals, including synthetic cryolite. From fluorosilicic acid, fluorine values are precipitated as sodium fluorosilicate by treating it with sodium salts. Sodium fluorosilicate becomes starting point for the production of synthetic cryolite.

For manufacture of synthetic cryolite from sodium fluorosilicate, two routes are generally adopted in the country. In the first route, sodium fluorosilicate is reacted with ammonia and in other route, sodium fluorosilicate is reacted with soda ash.

Important known units producing synthetic cryolite are highlighted below:

1. Navin Fluorine International Ltd, Udhana-Navasari Road, Surat, Gujarat-395 023.
2. Navin Fluorine International Ltd, Agra-Mumbai Road, Dewas, Madhya Pradesh-455 002.
3. Tanfac Industries Ltd, Kudikadu, Cuddalore, Tamil Nadu-607005.
4. Harshil Industries Sarigam, Vapi, Gujarat-396195.
5. Triveni Interchem Pvt. Ltd GIDC, Vapi, Gujarat.
6. S.B. Chemicals, GIDC, Char Rasta, Vapi, Gujarat-396195.

Navin Fluorine International Ltd is one of the largest manufacturers of speciality fluorochemicals comprising synthetic cryolite during 2016-17. NFIL produced 9,234 tonnes and 9,878 tonnes of synthetic cryolite in 2015-16 and 2016-17 respectively along with Aluminium Fluoride & Fluorocarbon gases.

It is also understood that Triveni Chemicals, S.B. Chemicals, Jay Intermediates & Chemicals (Vapi, Gujarat), Madras Fluorine Pvt. Ltd (Manali, Chennai, Tamil Nadu) and Tarun Fluo-Chem Pvt. Ltd, (Delhi) manufacture synthetic cryolite besides other fluorine chemicals. They also manufacture potassium cryolite (K_3AlF_6) which is a foundry flux and used in welding, chemicals and explosives.

CRYOLITE

The total installed capacity of aluminium fluoride in Organised Sector was about 25,600 tonnes per annum.

SPECIFICATIONS

The Indian Standard Specifications of cryolite for use in Aluminium Industry defined vide IS - 5893 : 1989 (Second Revision; reaffirmed 2008) are as follows:

Constituents (on dry basis)	Specification
F	53% min.
Na	31 to 34%
Al	13 to 15%
SiO ₂	0.20% max.
Fe ₂ O ₃	0.10% max.
CaF ₂	0.06% max.
Al ₂ O ₃	1.00% max.
SO ₃	0.50% max.
P ₂ O ₅	0.01% max.
Loss on Ignition (LOI)	0.50% max.
NaF/AlF ₃ (by mass)	1.45 max. (ratio required to maintain in acidic region)

- Note:**
- LOI is to be determined at 550°C for 60 minutes.
 - Moisture should not be more than 0.20% when determined at 110 ± 5°C.

CONSUMPTION

The consumption of cryolite is nowadays not estimated because many industries prefer the use of synthetic cryolite instead of natural cryolite. However, consumption was reported earlier in bonded abrasives as a filler, insecticides, porcelaneous glass and salts of sodium and aluminium.

USES AND TECHNOLOGY

The commercial application of cryolite is confined mainly to aluminium metallurgy where it is used as an electrolyte in the reduction of alumina to aluminium metal by the Hall-Heroult process. Alumina is a bad conductor of electricity and its melting point is 2,348 °C. It is very expensive to carry out

electrolysis at this temperature. To facilitate electrolysis, alumina is dissolved in molten cryolite as it lowers the melting point. Further, addition of certain additives, such as, aluminium fluoride improve the physical and electrical properties of the electrolyte, besides lowering the melting point. The amount that is added is, however, limited as it also causes reduction in electrical conductivity. Addition of calcium fluoride (CaF₂) further depresses the melting point with less adverse effect on conductivity. In contrast to this advantage, too much CaF₂ raises the density of the melt closer to that of liquid aluminium metal, thus inhibiting the separation of metal from electrolyte. The substituent, sodium fluoride, though is known to improve the density and conductivity, it also affects current efficiency.

A compromise made on all these factors has led to the following general composition of the bath to be in use – 80-85% cryolite, 5-7% AlF₃, 5-7% CaF₂, 0-7% LiF and 2-8% Al₂O₃. The electrolyte bath tends to deplete AlF₃ content of cryolite during the process. Hence, the composition of the electrolyte has to be adjusted regularly by addition of AlF₃.

In aluminium refining, high density electrolyte capable of floating aluminium is required. For this purpose, barium fluoride is used to raise density. Aluminium fluoride can be used to improve current efficiency of cryolite bath.

Cryolite is obtained as a by-product during the production of phosphatic fertilizer/phosphoric acid. When utilised in the Aluminium Industry, necessary precautions are observed as even 0.01% P in the electrolyte could cause 1-1.5% reduction in current efficiency in the production process of aluminium.

Other metallurgical uses of cryolite are in aluminising steel, in compounding of welding rod coatings and as fluxes. In glass, cryolite functions as a powerful flux because of its excellent solvent power for oxides of silicon, aluminium & calcium and for its ability to reduce melt viscosity at lower melting temperatures. Cryolite is used as a filler for resin-bonded grinding wheels in Abrasive Industry to impart longer life. Sodium fluoride (NaF) or fluorosilicic acid is also used for this purpose. Cryolite is used in certain nitrocellulose-based gun propellants required in small-calibre weapons, cannons and small & large rockets.

FOREIGN TRADE

Exports

In 2017-18, exports of Sodium Hexafluoroaluminate decreased marginally to 70 tonnes from 96 tonnes in the previous year. Saudi Arabia (39%), Iran (27%) and Turkey (26%) were the main buyers from India in 2016-17 (Table-1).

Imports

Imports of Sodium Hexafluoroaluminate in 2017-18, decreased drastically to 8,293 tonnes from 29,796 tonnes in the previous year. Saudi Arabia (36%), Australia (12%) and Norway (10%) were the main suppliers to India (Table-2).

**Table – 1 : Exports of Sodium Hexafluoroaluminate
(By Countries)**

Country	2016-17		2017-18	
	Qty (t)	Value (`'000)	Qty (t)	Value (`'000)
All Countries	96	6293	70	5438
Iran	40	2784	19	1436
Saudi Arabia	30	1696	27	1634
Turkey	19	1186	18	1133
Uganda	2	186	2	212
Pakistan	1	97	1	223
Indonesia	++	62	3	780
USA	++	59	-	-
Russia	-	-	++	16
Tunisia	-	-	++	1
Vietnam	-	-	++	3
Other countries	4	223	-	-

**Table – 2 : Imports of Sodium Hexafluoroaluminate
(By Countries)**

Country	2016-17		2017-18	
	Qty (t)	Value (`'000)	Qty (t)	Value (`'000)
All Countries	29796	447618	8293	240861
Canada	8589	110531	628	13192
Saudi Arabia	8389	105337	2962	61760
China	893	56337	741	46421
Argentina	3004	47736	702	15113
Norway	581	6938	835	17346
Germany	297	20343	511	31956
Chinese Tapei/Taiwan	-	-	362	13645
Italy	-	-	160	10539
Australia	542	8948	999	18099
Japan	++	77	80	4980
Other countries	7501	91371	313	7810

CRYOLITE

FUTURE OUTLOOK

The future of cryolite is dependent upon its use in the Aluminium Industry. Increased usage of aluminium and high performance fluoropolymers in automobiles will drive growth in inorganic and specially fluorochemicals.

It is learnt that some US firms have registered success in their research and pilot plant tests for the production of aluminium directly from the mineral bauxite without the intermediate process of reduction cell. Viability of this may probably eliminate the use of cryolite in the near future.

