

DOLOMITE



# **Indian Minerals Yearbook 2021**

**(Part- III : Mineral Reviews)**

**60<sup>th</sup> Edition**

## **MINOR MINERALS 30.6 DOLOMITE**

**(ADVANCE RELEASE)**

**GOVERNMENT OF INDIA  
MINISTRY OF MINES  
INDIAN BUREAU OF MINES**

Indira Bhavan, Civil Lines,  
NAGPUR – 440 001

PHONE/FAX NO. (0712) 2565471  
PBX : (0712) 2562649, 2560544, 2560648  
E-MAIL : [cme@ibm.gov.in](mailto:cme@ibm.gov.in)  
Website: [www.ibm.gov.in](http://www.ibm.gov.in)

**April, 2023**

## 30-6 Dolomite

**D**olomite ( $\text{CaCO}_3 \cdot \text{MgCO}_3$ ) theoretically contains  $\text{CaCO}_3$  (54.35%) and  $\text{MgCO}_3$  (45.65%) or  $\text{CaO}$  (30.4%),  $\text{MgO}$  (21.9%) and  $\text{CO}_2$  (47.7%). However, in nature, dolomite is not available in this exact proportion. Hence, in commercial parlance, the rock containing 40–45%  $\text{MgCO}_3$  is usually called dolomite. Dolomite rock that contains either calcite or a mixture of calcite & magnesite in addition to dolomite is called "Dolomitic Limestone". It is grouped under flux & construction minerals and is important for Iron & Steel and Ferroalloys industries. Dolomite occurrences are widespread in almost all parts of the country.

Removal of overburden is imperative in a mining activity, which leads to cutting of trees and deforestation. The statute provides directives for reclamation of the mined out areas and plantation of trees to regain the aesthetics of the degraded land. A study in this regard was undertaken to get an idea of afforestation efforts and success rate.

Mineral dolomite is found in almost all States and it is mostly mined by opencast method of mining.

### RESERVES/RESOURCES

Dolomite occurrences are widespread in the country. As per NMI data, based on UNFC system, as on 1.4.2015, the total reserves/resources of dolomite has been placed at 8,415 million tonnes, out of which 677.8 million tonnes are placed under Reserves category and the balance 7,737 million tonnes under Remaining Resources category. Gradewise, BF/sintering grade alone accounted for 24% resources followed by S.M.S. (OH), S.M.S. (L.D.) & S.M.S. (O.H. & L.D. Mixed) (25%); refractory (8%), B.F. & S.M.S. mixed (5%); and glass (3%). Others, Unclassified, Not-known, B.F., S.M.S. & refractory grades together accounted for the remaining 35% resources. Major share of about 88% resources is found distributed in eight States, namely, Madhya Pradesh (27%), Andhra Pradesh (15%),

Chhattisgarh (11%), Odisha (10%), Karnataka & Rajasthan (7% each), Gujarat (6%) and Maharashtra (5%). The remaining 12% resources are distributed in Arunachal Pradesh, Jharkhand, Haryana, Sikkim, Tamil Nadu, Telangana, Uttarakhand, Uttar Pradesh and West Bengal. Gradewise and Statewise reserves/resources of dolomite are furnished in Table-1.

### EXPLORATION & DEVELOPMENT

The exploration & development details, if any, are covered in the Review on "Exploration & Development" under "General Reviews".

### PRODUCTION

As per Govt of India Notification S.O. 423(E), dated 10<sup>th</sup> February 2015, 'dolomite' has been declared as 'Minor Mineral', hence the producers report the production data directly to the respective States and not to IBM. However, efforts were made to collect this information through correspondence with the State Directorates of Mining and Geology of individual States or by visiting their websites. But data of only a few States could be collected. All possible information/data that could be gathered has been presented in this Review.

Statewise production of dolomite during 2018-19 to 2020-21 is furnished in Table-2.

**Table- 2 : Statewise Production of Dolomite**

(In tonnes)

State	Year		
	2018-19	2019-20	2020-21
Andhra Pradesh	2034682	2039342	2128467
Gujarat	1455352	-	-
Telangana	653025	518052	-
Maharashtra	468890	465667	-
Rajasthan	285000	177000	117875
Karnataka	628114	913373	923669

*Source: As received from State DGMS and their websites*

*Note : " - " NA*

DOLOMITE

**Table – 1 : Reserves/Resources of Dolomite as on 1.4.2015  
(By Grades/States)**

Grades/States	Reserves										Remaining Resources					Total (B)	Resources (A+B)			
	Proved STD111		Probable		Total (A)		Feasibility STD211		Pre-feasibility STD221 STD222		Measured STD331		Indicated STD332		Inferred STD333			Reconnaissance STD334		
	STD121	STD122	STD121	STD122	STD121	STD122	STD221	STD222	STD331	STD332	STD333	STD334	STD335	STD336	STD337			STD338	STD339	STD340
<b>All India : Total</b>	<b>431750</b>	<b>107364</b>	<b>138770</b>	<b>677884</b>	<b>372515</b>	<b>323183</b>	<b>537932</b>	<b>307103</b>	<b>757005</b>	<b>5215075</b>	<b>224194</b>	<b>7737007</b>	<b>8414891</b>							
<b>By Grades</b>																				
B.F./Sintering	114238	7657	55233	177128	82335	77121	139875	185566	412641	863924	34946	1796407	1979535							
S.M.S.(O.H.)	64004	26454	13147	103605	87822	27618	36350	32509	123316	863484	76707	1247806	1351411							
S.M.S.(L.D.)	39244	4317	12740	56300	27207	9680	159913	8697	5464	136145	80	347186	403487							
S.M.S.(O.H.& L.D mixed)	50417	328	2539	53284	7142	44258	9977	30718	4000	184470	969	281534	334818							
B.F. & S.M.S. mixed	43316	670	10031	54017	32665	14474	2811	18140	35000	226370	-	329461	383478							
Refractory	8305	6457	4097	18859	34984	68817	51803	-	271	515375	2994	674244	693103							
B.F., S.M.S.& Refractory	-	-	-	-	-	1797	1258	-	-	5387	-	8441	8441							
Glass	285	25792	369	26446	4392	22136	44773	2093	1297	127978	-	202668	229114							
Others	70539	17960	16122	104622	68632	33909	41387	28073	47783	124737	4969	349490	454112							
Unclassified	40599	17609	23720	81928	21639	21593	25698	1099	58954	591618	7674	728276	810203							
Not-known	803	122	770	1695	5697	1780	24087	207	68279	1575587	95856	1771493	1773188							
<b>By States</b>																				
Andhra Pradesh	86134	11371	17539	115045	176477	31908	38234	22373	77	910217	4301	1183677	1298722							
Arunachal Pradesh	-	-	-	-	-	-	-	-	204	77633	-	77837	77837							
Chhattisgarh	34465	48130	11623	94218	29294	80865	24512	150795	24412	511610	1950	823439	917657							
Gujarat	34862	15934	20829	71625	11947	27064	68785	20263	63780	280592	-	472431	544056							
Haryana	-	-	-	-	1692	6037	3722	-	-	16183	-	27633	27633							
Jharkhand	4510	-	6720	11230	10620	350	860	-	-	1857	-	13686	24916							
Karnataka	28609	5910	6093	40612	16264	6684	9202	8519	76244	455337	13482	585731	626344							
Madhya Pradesh	23765	10078	18714	52557	33798	94599	102857	33030	295222	1584534	114799	2258839	2311395							
Maharashtra	8301	4346	7768	20416	13986	16036	7371	-	18050	339141	2994	397578	417994							
Odisha	109551	6421	34839	150811	42521	33896	110904	48535	46683	330660	85884	699082	849892							
Rajasthan	57910	4579	13994	76483	20483	10807	121082	16132	25480	327838	784	522607	599089							
Sikkim	-	-	-	-	-	-	-	-	-	2756	-	2756	2756							
Tamil Nadu	-	-	-	-	-	-	-	2010	135	-	-	2145	2145							
Telangana	42072	-	651	42723	2869	1594	1944	-	132511	6380	-	145298	188021							
Uttar Pradesh	-	-	-	-	-	12622	-	3500	-	66230	-	82352	82352							
Uttarakhand	1570	594	-	2165	36	721	371	1946	981	199834	-	203888	206053							
West Bengal	-	-	-	-	12528	-	48000	-	73226	104275	-	238029	238029							

Figures rounded off.

## USES & SPECIFICATIONS

Dolomite after calcination is used for refractory purposes (as a substitute of magnesite refractories) in linings of furnaces like basic open-hearth steel furnaces and basic Bessemer converters.

High purity dead-burnt dolomite bricks are required for lining LD furnaces, while mini-steel plants generally require dolomite for fettling and refractory purposes. Like limestone, dolomite is used as a flux in iron & steel, ferroalloys and glass works. Few steel plants have dispensed with the use of dolomite in blast furnaces and its use in the preparation of self-fluxing sinters is found adequate for blast-furnace charge.

It is useful in the recovery of magnesia and also in the manufacture of magnesium metal; it finds important application in the manufacture of basic magnesium carbonate (termed 'technical carbonate', 'block magnesia' or 'magnesia alba') used in pipe and boiler coverings as heat insulation, in pharmaceutical, rubber, chemical Industries, paper, leather, glass, potteries and high-magnesium limes. In agriculture, it is used as a soil conditioner to neutralise acidity. Regular application of dolomite improves crop yields owing to its neutralisation potential. It finds use as a filler in fertilizers, paints & varnishes and for suppression of dust in coal mines. It is also used as a building stone and in the making of flooring tiles as chips & powder.

Generally, insolubles like  $\text{SiO}_2$ ,  $\text{Fe}_2\text{O}_3$  and  $\text{Al}_2\text{O}_3$  are considered deleterious constituents of dolomite for any industrial use. It is essential that these insolubles should be as low as possible. High purity dolomite with less than one per cent insolubles is preferred for making refractory bricks which are used in the lining of LD furnaces.

Similarly, high-grade dolomite containing low iron (less than 0.15%) is required in Glass Industry. BIS has prescribed the specifications of dolomite used in Glass Industry vide IS: 997-1973; (First Revision; Reaffirmed 2008). Specifications for flux grade dolomite for use in Iron & Steel Industry have been revised and are prescribed in IS: 10346 - 2004 (second revision, Reaffirmed 2009), while specifications of dolomite for Refractory Industry are prescribed in IS: 14296 - 1995 (Reaffirmed 2010). IS: 15366 - 2003 (Reaffirmed 2009) lays down the specifications of dolomite for Paint Industry.

## FUTURE OUTLOOK

Over 95% of the total production of dolomite finds outlet mainly in Iron & Steel and allied industries. The importance of high purity dead-burnt dolomite bricks for lining LD furnaces has gained ground due to LD process of steel making. At the same time, a few of the steel plants have dispensed with the use of dolomite in blast furnace. Mini-steel plants generally require dolomite for fettling and refractory purpose only.

The resources of the Refractory grade dolomite in the country are meagre and this type of material is in short supply though the demand for it is very high especially for producing tar-bonded dolomite bricks. Therefore, intensive search is needed in non-Himalayan regions for locating deposits of massive non-crystalline dolomite, containing less than 2.5%  $\text{R}_2\text{O}_3$  for use in tar-dolomite bricks required for lining of LD steel furnaces.