

LATERITE



Indian Minerals Yearbook 2021

(Part- III : Mineral Reviews)

60th Edition

MINOR MINERALS 30.14 LATERITE

(ADVANCE RELEASE)

**GOVERNMENT OF INDIA
MINISTRY OF MINES
INDIAN BUREAU OF MINES**

Indira Bhavan, Civil Lines,
NAGPUR – 440 001

PHONE/FAX NO. (0712) 2565471
PBX : (0712) 2562649, 2560544, 2560648
E-MAIL : cme@ibm.gov.in
Website: www.ibm.gov.in

April, 2023

30-14 Laterite

Laterite (from the Latin word *later*, meaning "brick" or "tile") is a surface formation that is enriched in iron and aluminium. Found mainly in hot, wet tropical areas, it develops by intensive and long-lasting weathering of the underlying parent rock. The mineralogical & chemical composition of laterite depends on their parent rock. Due to the presence of iron oxides, lateritic soils are red in colour ranging from light bright to brown shades. The term 'laterite' was originally used for highly ferruginous deposits, first observed in Malabar Region of coastal Kerala and Dakshina Kannada & other parts of Karnataka. It is a highly weathered material, rich in secondary oxides of iron, aluminium or both. It is either hard or capable of hardening on exposure to moisture and drying.

Laterite and bauxite show a tendency to occur together. Aluminous laterites and ferruginous bauxites are quite common. The most common impurity in both is silica. Laterite gradually passes into bauxite with decrease in iron oxide and increase in aluminium oxide. The laterite deposits may be described on the basis of the dominant extractable minerals in it: (i) aluminous laterite (bauxite), (ii) ferruginous laterite (iron ore), (iii) manganiferous laterite (manganese ore), (iv) nickeliferous laterite (nickel ore) and (v) chromiferous laterite (chrome ore). Laterite with $Fe_2O_3:Al_2O_3$ ratio more than one, and $SiO_2:Fe_2O_3$ ratio less than 1.33 is termed as ferruginous laterite, while that having $Fe_2O_3:Al_2O_3$ ratio less than one and $SiO_2:Al_2O_3$ ratio less than 1.33 is termed as aluminous laterite.

Laterite can be considered as polymetallic ore as it is not only the essential repository for aluminium, but also a source of iron, manganese, cobalt, nickel and chromium. Furthermore, it is the home for several trace elements like gallium and vanadium which can be extracted as by-products.

RESERVES/RESOURCES

Laterite occurrences are widespread in the country. Almost all Indian bauxite deposits are associated with laterite, except those in Jammu & Kashmir. Laterite generally occurs as capping on the hills and plateaus of Madhya Pradesh and in some States of the Deccan peninsula at altitudes ranging from coastal to 2,000 m with thickness up to 60 m.

As per the NMI database based on UNFC System as on 1.04.2015, the total reserves/resources of laterite were estimated at 706 million tonnes. Out of these, 124 million tonnes are placed under Reserves category and 581 million tonnes are under Remaining Resources category. Major share of about 73% resources is located in two States, namely, Madhya Pradesh (56%) and Rajasthan (17%). The remaining 27% of resources are spread over in the States of Andhra Pradesh, Kerala, Gujarat, Maharashtra and Jharkhand. Gradewise and Statewise reserves/resources are furnished in Table- 1.

EXPLORATION & DEVELOPMENT

The exploration & development details, if any, are covered in the Review on "Exploration & Development" under "General Reviews".

PRODUCTION

As per Govt of India Notification S.O. 423(E), dated 10th February 2015, 'laterite' has been declared as 'Minor Mineral', hence the producers report the production data directly to the respective States and not to IBM. However, efforts were made to collect this information through correspondence with the State Directorates of Mining and Geology of individual States or visiting their websites. But data of only a few states could be collected. All possible information/data that could be gathered has been presented in this Review.

Statewise production of laterite from 2018-19 to 2020-21 is furnished in Table-2.

Table-2 : Statewise Production of Laterite

State	Year		
	2018-19	2019-20	2020-21
Andhra Pradesh	2260896	707730	71866
Telangana	3837982	3471995	-
Maharashtra	1809659	2252671	-
Gujarat	14670	-	-
Goa	930*	-	-
Kerala*	3007297	-	-
Karnataka	108468	327842	295060

Source: As received from State DGMs and their websites

*Note : " - " NA, *in cu. m*

** : Figure relates to laterite (building) only.*

**Table – 1 : Reserves/Resources of Laterite as on 1.4.2015
(By Grades/States)**

(In '000' tonnes)

Grade/State	Reserves			Remaining Resources				Total Resources (A+B)		
	Proved STD111	Probable STD121 STD122	Total (A)	Feasibility STD211	Pre-feasibility STD221 STD222	Measured STD331	Indicated STD332		Inferred Reconnaissance STD333 STD334	Total (B)
All India : Total	98598	12527 13608	124733	49655	8960 22724	3532	2626	243535 250787	581819	706552
By Grade										
Unclassified	98598	12527 13608	124733	49655	8960 22724	3532	2626	243535 250787	581819	706552
By States										
Andhra Pradesh	13574	680 1710	15964	23238	5107 2244	24	1107	889 -	32608	48572
Gujarat	36019	- 399	36418	8095	- 1467	-	-	- -	9562	45981
Jharkhand	-	- -	-	-	- -	-	-	570 -	570	570
Kerala	-	- 1156	1156	953	- -	-	-	- 16717	17670	18826
Madhya Pradesh	12534	3355 7917	23807	8715	1631 16077	3189	1519	167527 169678	368336	392143
Maharashtra	-	278 -	278	2215	1393	319	-	7577 -	11903	12181
Odisha	-	- -	-	-	- -	-	-	- 1227	1227	1227
Rajasthan	-	- -	-	-	- -	-	-	60490 62860	123350	123350
Telangana	36471	8213 2426	47110	6439	828 2536	-	-	6483 305	16591	63701

Figures rounded off.

USES & SPECIFICATIONS

Indian Standards code IS 3620-1979 provides specifications and standards for laterite masonry construction in India. Unique material properties and regional variations have rendered laterite stone as subject of controversy. The engineering characteristics of laterite from Malabar region of western India have been reflected in research studies conducted and were established in several other published studies.

The compact and ferruginous variety of laterite is used widely as a building stone and road metal. It cannot withstand heavy pressure hence, laterite is used in construction of light structures, partition walls, boundary walls, etc. Laterite as a building stone possesses one advantage that it is soft when quarried and can be easily cut and dressed into blocks and bricks which on exposure to air become hard.

The industrial use of laterite is in the Cement Industry. It is used as an additive for lowering the clinkerisation temperature and supplementing aluminous and iron contents required in the

manufacture of cement. It is also reported that laterite is capable of removal of phosphorus from solutions and percolating columns of laterite remove cadmium, chromium and lead to very low concentrations.

FUTURE OUTLOOK

In India, though the resources of laterite are vast and are available in abundance, the work in respect of systematic exploration and estimation of resources have been restricted. There seems to be no major change in the end-use pattern of laterite.

Laterite is widely used as a building stone and road metal. Laterite is a weak stone, but can be used for masonry construction. The property of laterite can be enhanced by suitable water proofing treatments. Long-term study is required to find an optimum size for its varied masonry applications.

The consumption of laterite in cement has risen due to increased demand of cement in the country. The plausibility of diverse application of laterite in future could be in the realm as a viable source for metallic minerals like iron, aluminium, chromite and of trace elements like gallium and vanadium.